

OK Flux 10.26

OK Flux 10.26 is a high basic, agglomerated Ni-, Cr- and Mo-adding flux designed for single layer electrosag strip cladding solution. The flux has very good welding characteristics gives a smooth bead appearance and easy slag removal. When combined with Exaton 19.13.4.L, it delivers a 317L weld deposit chemistry typically required on pressure vessels, heat exchangers, shafts, industrial piping in the chemical, petrochemical and marine industries.

Specifications	
Classifications	EN ISO 14174 : ES A FB 2B 54 91 NiMo DC
Slag Type	Fluoride basic
Alloy Transfer	Nickel, chromium and molybdenum
Density	nom: 1.2 kg/dm ³
Basicity Index	nom: 3.0

Classifications	
Wire	AWS/EN
19.13.4.L ESW	A5.9:EQ317L/ 14343:19 13 4 L
OK Band 316L	A5.9:EQ316L/ 14343-A:B 19 12 3 L

Approvals	
Combined with Wire	
*Selected production units only. Please contact ESAB for more information. Visit esab.com to download specific flux/wire combination fact sheets for more details.	

Typical Wire Composition %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
19.13.4.L ESW									
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	-
OK Band 316L									
0.01	1.73	0.4	-	-	12.6	18.5	2.9	-	0.05

Typical Wire Composition %									
Ferrite FN									
19.13.4.L ESW									
7									
OK Band 316L									
7									

Typical Weld Metal Analysis %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
19.13.4.L ESW									
0.02	1.0	0.5	0.01	0.02	13.8	19	3.4	0.07	-
OK Band 316L									
-	-	-	0.01	0.02	-	-	-	0.1	-
OK Band 316L DC+, 1200A, 24V, 16-18 cm/min									
0.02	1.2	0.2	-	-	12.8	19.0	2.7	-	0.05

Typical Weld Metal Analysis %	
Ferrite FN	FN WRC-92
19.13.4.L ESW	
7	-
OK Band 316L DC+, 1200A, 24V, 16-18 cm/min	

OK Flux 10.26

Typical Weld Metal Analysis %

Ferrite FN	FN WRC-92
-	7