

Exaton 317/317L

317/317L is a chromium-nickel-molybdenum strip electrode used for electro-slag welding (ESW) or submerged arc welding (SAW) to deposit a second layer corrosion resistant alloy of 19%Cr/13%Ni/4%Mo composition on carbon- and low alloyed steels. The buffer layer is deposited using an over-alloyed consumable, such as 309LMo or 309L

Specifications

Classifications	EN ISO 14343-A : B 19 13 4 L SFA/AWS A5.9 : EQ317L
------------------------	---

Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	FN WRC-92
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	7