

## **Exaton 309LNb**

309LNb is a niobium stabilized chromium-nickel strip electrode used for submerged arc welding (SAW) to deposit a buffer layer of stabilized corrosion resistant alloy of 19%Cr/9%Ni composition on carbonand low alloyed steels. In high speed electro-slag welding (ESW) it can be used for single layer deposits of 347 composition on carbon- and low alloyed steels. It can also be combined with 347L for surfacing of two layer overlays.

Specifications						
Classifications	EN ISO 14343-A : B 23 12 Nb					
	SFA/AWS A5.9 : EQ?309LNb?					

Typical Wire Composition %											
С	Mn	Si	S	P	Ni	Cr	Мо	Cu	Nb		
<=0.02	2	0.3	<=0.020	<=0.020	12.5	24	<=0.3	<=0.3	0.75		

Typical Wire Composition %	
FN WRC-92	
22	