

Dual Shield II 711X

Dual Shield II 711X is an all-position flux cored wire that displays exceptional impact properties in combination with CO₂ shielding gas. This flux cored wire was developed to join low and medium carbon steels where higher impacts and toughness are required. As with all X Series wires, Dual Shield II 711X offers higher top-end current levels for out-of-position welding, broader operating ranges and higher deposition rates in out-of-position applications. Applications include construction, shipbuilding, rail car, light and heavy equipment, and general fabrication where exceptional impacts are required. Weld metal analysis is similar to Atom Arc 7018 and Atom Arc 7018-1.

Specifications

Classifications	AWS A5.20 : E71T-CJ-DH8/T-9CJ-DH8/T-12CJ-DH8 AWS A5.36 : E71T1-C1A4-CS2-DH8
Approvals	ABS 3SA,3YSA ASME SFA 5.20 AWS A5.20 : E71T-1CJH8/T-9CJH8/T-9M H8/T-12CJH8 AWS A5.20 : E71T-CJH8/T-9CJH8/T-12CJH8 CERTIFIED BY C.W.B. - CSA W48 D.N.V.- III YMS(H10) DNV IIIY40MS (H10) L.R. - 3S,3YS
Industry	Railcars Civil Construction Industrial and General Fabrication Ship/Barge Building

Approvals are based on factory location. Please contact ESAB for more information.

Typical Tensile Properties

Yield Strength	Tensile Strength	Elongation
100% CO₂		
540 MPa (78 ksi)	595 MPa (86 ksi)	29 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
100% CO₂		
As Welded	-18 °C (0 °F)	130 J (96 ft-lb)
As Welded	-40 °C (-40 °F)	49 J (36 ft-lb)
As Welded	-29 °C (-20 °F)	107 J (79 ft-lb)

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni
100% CO₂					
0.04	1.4	0.4	0.010	0.012	0.4

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Efficiency (%)	TTW Dist.	Deposition Rate
100% CO₂						
1.6 mm (1/16 in.)	210 A	24 V	444.5 cm/min (175 in./min)	83 %	19 mm (3/4 in.)	2.58 kg/h (5.68 lbs/h)
1.6 mm (1/16 in.)	162 A	22.5 V	356 cm/min (140 in./min)	84 %	19 mm (3/4 in.)	2.04 kg/h (4.50 lbs/h)
1.4 mm (.052 in.)	172 A	22 V	559 cm/min (220 in./min)	83 %	15.8 mm (5/8 in.)	2.32 kg/h (5.11 lbs/h)
1.6 mm (1/16 in.)	245 A	25 V	546 cm/min (215 in./min)	84 %	19 mm (3/4 in.)	3.19 kg/h (7.03 lbs/h)

Dual Shield II 711X

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Efficiency (%)	TTW Dist.	Deposition Rate
1.2 mm (.045 in.)	184 A	24 V	800 cm/min (315 in./min)	84 %	15.8 mm (5/8 in.)	3.10 kg/h (6.84 lbs/h)
1.2 mm (.045 in.)	112 A	20.5 V	444.5 cm/min (175 in./min)	86 %	15.8 mm (5/8 in.)	1.46 kg/h (3.22 lbs/h)
1.2 mm (.045 in.)	140 A	22 V	571.5 cm/min (225 in./min)	84 %	15.8 mm (5/8 in.)	2.20 kg/h (4.85 lbs/h)
1.4 mm (.052 in.)	220 A	24 V	762 cm/min (300 in./min)	83 %	15.8 mm (5/8 in.)	3.20 kg/h (7.06 lbs/h)
1.6 mm (1/16 in.)	270 A	27 V	635 cm/min (250 in./min)	84 %	19 mm (3/4 in.)	3.77 kg/h (8.32 lbs/h)
1.2 mm (.045 in.)	235 A	26.5 V	1079.5 cm/min (425 in./min)	85 %	15.8 mm (5/8 in.)	3.58 kg/h (7.89 lbs/h)
1.4 mm (.052 in.)	260 A	26.5 V	952.5 cm/min (375 in./min)	84 %	15.8 mm (5/8 in.)	4.11 kg/h (9.06 lbs/h)