

OK Tigrod 13.37

A copper coated, low-alloyed, chromium-molybdenum (9% Cr, 1% Mo), rod for GTAW of high temperature steels and steels for hot hydrogen service, especially in oil refineries. The electrode is a plain ER505 type.

Specifications

Classifications	EN ISO 21952-A : W CrMo9 EN ISO 21952-B : W 55 9C1M SFA/AWS A5.28 : ER80S-B8
Approvals	NAKS/HAKC : 2.0 - 2.4 mm

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Alloyed steel (9 % Cr - 1 % Mo) "ER505"
Shielding Gas	I1 (EN ISO 14175)

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
Enhanced testing temperature.			
Stress relieved+ 2 hour(s) 760 °C	410 MPa	480 MPa	18 %
Stress Relieved 2 hour(s) 760 °C	430 MPa	500 MPa	17 %
Stress relieved++ 2 hour(s) 760 °C	350 MPa	390 MPa	22 %
Ar (I1) EN			
Stress Relieved 2 hour(s) 760 °C	540 MPa	660 MPa	26 %
Stress relieved+ 4 hour(s) 735 °C	560 MPa	680 MPa	22 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
Ar (I1) EN		
Stress relieved+	-60 °C	50 J
Stress relieved+	-40 °C	130 J
Stress Relieved	-20 °C	140 J
Stress relieved+	-20 °C	150 J
Stress Relieved	-40 °C	120 J
Stress Relieved	-60 °C	90 J

Typical Wire Composition %

C	Mn	Si	Ni	Cr	Mo
0.06	0.52	0.45	0.23	8.66	1.00

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Cr	Mo
0.1	0.5	0.4	0.005	0.01	8.6	0.9

Recommended Welding Parameters

Current	Wire Diameter
60-200 A	2.0 mm
100-220 A	2.4 mm