

OK Tigrod NiCrMo-3

Bare corrosion and heat-resisting Ni-Cr-Mo rods for welding of high alloyed heat-resisting and corrosion resisting materials, 9%Ni-steels and similar steels with high notch toughness at low temperatures. Also for joining of dissimilar metals of the types mentioned. The weld metal has very good mechanical properties at high and low temperatures. Good resistance to pitting and stress corrosion.

Specifications		
Classifications	SFA/AWS A5.14 : ERNiCrMo-3 EN ISO 18274 : S Ni 6625	
Approvals	BV : ERNiCrMo-3 DNV-GL : 2.4 mm VdTÜV : 12460	

Approvals are based on factory location. Please contact ESAB for more information.

Аlloy Туре	Alloyed nickel (Ni + 22 % Cr + 9 % Mo - 3.5 % Nb)
Shielding Gas	I1, I3, R1 (EN ISO 14175)

Typical Tensile Properties				
Condition	Yield Strength	Tensile Strength	Elongation	
As Welded	550 MPa	780 MPa	40 %	

Typical Charpy V-Notch Properties				
Condition	Testing Temperature	Impact Value		
As Welded	-196 °C	100 J		

Typical Wire Composition %							
С	Mn	Si	Ni	Cr	Мо	Fe	Nb+Ta
0.02	0.04	0.06	Bal	22.7	8.6	0.3	3.5