

Exaton 24.13.L

Exaton 24.13.L is a chromium-nickel strip electrode used for submerged arc welding (SAW) and high speed electro-slag welding (ESW) to deposit a buffer overlay of corrosion resistant alloy of 19%Cr/9%Ni composition on carbon- and low alloyed steels. It is combined with Exaton 19.9.L for surfacing of two layer overlays.

Spezifikationen

Klassifikationen	EN ISO 14343-A : B 23 12 L SFA/AWS A5.9 : EQ309L
Zulassungen	CE : EN 13479 UKCA : EN 13479

Zulassungen basieren auf dem Werksstandort. Bitte kontaktieren Sie ESAB für weitere Informationen.

Drahtzusammensetzung

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	FN WRC-92
<=0.015	1.8	0.35	<=0.015	<=0.015	13	23.5	<=0.3	<=0.1	15