

OK 316L

Extra low carbon stainless steel electrode for welding steels of the 18Cr12Ni2.8Mo-type. Also suitable for welding stabilized steels of similar composition except when full creep resistance of the base material is to be matched.

Specifications

Classifications	SFA/AWS A5.4 : E316L-16 JIS Z 3221 : D316L-16
------------------------	--

Welding Current	AC, DC+
Ferrite Content	FN 3-10
Alloy Type	CrNi
Coating Type	Acid-Rutile

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
AWS			
As Welded	485 MPa	590 MPa	42 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
AWS		
As Welded	-60 °C	42 J
As Welded	20 °C	60 J

Typical Weld Metal Analysis %

C	Mn	Si	Ni	Cr	Mo	N	Ferrite FN
0.02	0.6	0.8	11.0	18.1	2.6	0.10	6

Deposition Data

Diameter	Current	Voltage	Efficiency (%)	Fusion time per electrode at 90% I max	Deposition Rate
2.5 x 300.0 mm	45-90 A	29 V	55 %	45 sec	0.9 kg/h
3.2 x 350.0 mm	60-125 A	30 V	55 %	57 sec	1.4 kg/h
4.0 x 350.0 mm	70-190 A	32 V	56 %	57 sec	2.0 kg/h