

Dual Shield B6

Dual Shield B6 is an all-position flux cored electrode designed for using with 75% Ar / 25% CO₂ or 100% CO₂ shielding gas. Dual Shield B6 is intended for use on pipe and plate steels having a nominal 5% chromium - 0.5% molybdenum composition. These steels are typically used in process piping in the oil, gas, petrochemical, and marine industries.

Specifications	
Classifications	SFA/AWS A5.29 : E81T1-B6C SFA/AWS A5.29 : E81T1-B6M
Industry	Pipeline Petrochemical Power Generation

Alloy Type	Low Alloy 5% Cr, 0.5% Mo
------------	--------------------------

Typical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation
M21 Shielding Gas			
Stress Relieved 2 hour(s) 746 °C	580 MPa	676 MPa	20 %
C1 Shielding Gas			
Stress Relieved 2 hour(s) 746 °C	540 MPa	640 MPa	20 %

Typical Weld Metal Analysis %						
C	Mn	Si	S	P	Cr	Mo
0.08	0.60	0.50	0.006	0.01	4.70	0.50

Deposition Data				
Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.2 mm	150-310 A	28-34 V	5.08-15.24 m/min	1.91-5.31 kg/h