

Exaton Ni60

Exaton Ni60 welding wire is suitable for joining nickel-chromium-molybdenum nickel alloys and chromium-nickel-molybdenum steels with very high corrosion resistance in oxidizing, aqueous and high temperature environments such as 6Mo-steels, UNS N06625 (2.4856) and corresponding grades. It is also suitable for joining stainless steels and nickel alloys for high-temperature service. Exaton Ni60 can also be used for dissimilar joining of stainless steels to nickel alloys and for overlay welding. Applications for Exaton Ni60 are found in cryogenics, components subject to high temperature service up to 980°C (1800°F) such as aircraft ducting, engine exhaust systems, power boilers and recovery boilers and a diversity of seawater applications. The combination of strength and corrosion resistance over a wide range of temperatures is utilized in reaction vessels, line pipe distillation columns and heat exchangers. It is used for Submerged Arc Welding, for example in combination with the flux Exaton 15W.

Specificaties	
Classificaties	SFA/AWS A5.14 : ERNiCrMo-3 EN ISO 18274 : S Ni 6625 (NiCr22Mo9Nb) Werkstoffnummer : 2.4831
Goedkeuringen	VdTÜV : 03770

Goedkeuringen zijn gebaseerd op fabriekslocatie. Neem contact op met ESAB voor meer informatie.