

Exaton 25.10.4.LR

Exaton 25.10.4.LR is a covered electrode with rutile-basic coating used for welding of super-duplex (austenitic-ferritic) stainless steels of UNS S32750 and S32760 type (e.g. SAF 2507 and Zeron 100). The weld metal has excellent resistance against stress corrosion cracking, general- and pitting corrosion. It has also high resistance to erosion corrosion and corrosion fatigue. Spray transfer gives a bead with a finely rippled surface. There is little spatter and very good slag removal. The electrode has excellent arc stability and fast burn off rate with minimal stub loss. Typical applications include welding of austenitic-ferritic stainless steels such as SAF 2507, UNS S32750 (wrought) and UNS J93404 (cast) and other super-duplex steels, 25% chromium duplex stainless steels with PRE values between 37 and 40, dissimilar joints between duplex and carbon and low-alloy steels, SAF 2205 and corresponding duplex steels where the highest corrosion resistance is required.

Specificaties	
Classificaties	EN ISO 3581-A : E 25 9 4 N L R SFA/AWS A5.4 : E2594-16 Werkstoffnummer : (1.4410)
Goedkeuringen	CE : EN 13479 UKCA : EN 13479 VdTÜV : 07378

Goedkeuringen zijn gebaseerd op fabriekslocatie. Neem contact op met ESAB voor meer informatie.

Lasstroom	DC+, AC
Ferrietgehalte	FN 35-65
Legering Type	Austenitic-Ferritic CrNiMo
Coating Type	Rutile Basic

Typische Mechanische Eigenschappen			
Conditionering	Rekgrens	Treksterkte	Rek
ISO			
Zoals gelast	730 MPa	900 MPa	25 %

Kerfslageeigenschappen		
Conditionering	Testtemperatuur	Kerfslagwaarde
ISO		
Zoals gelast	20 °C	70 J
Zoals gelast	-40 °C	45 J

Typische lasmetaalanalyse (%)									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
0.03	1	0.5	<=0.025	<=0.03	9.5	25	4	0.09	0.25

Typische lasmetaalanalyse (%)	
FN WRC-92	PREN
45	>=42

Neersmeltgegevens					
Diameter	Ampère	Volt	Rendement (%)	Smelttijd per elektrode bij 90% I max	Neersmelt
2.5 x 300.0 mm	55-85 A	22 V	65 %	41 sec	0.9 kg/h
3.2 x 350.0 mm	70-110 A	22 V	63 %	67 sec	1.1 kg/h
4.0 x 350.0 mm	110-150 A	22 V	65 %	71 sec	1.4 kg/h