

Exaton 22.8.3.L

Exaton 22.8.3.L is a duplex stainless filler metal for welding duplex stainless steels. Weldability as well as properties of the all-weld metal is excellent. Corrosion resistance is equal to 904L in most applications. Exaton 22.8.3.L is used for welding of duplex stainless steels such as Alleima SAF 2205 and SAF 2304. It can also be used for welding of duplex stainless steels to carbon steel and for cladding. It is used for Submerged Arc Welding and the recommended flux is Exaton 15W.

Specificaties	
Classificaties	EN ISO 14343-A : S 22 9 3 N L SFA/AWS A5.9 : ER2209
Goedkeuringen	CE : EN 13479 UKCA : EN 13479

Goedkeuringen zijn gebaseerd op fabriekslocatie. Neem contact op met ESAB voor meer informatie.

Legering Type	Austenitic-ferritic (22.5 % Cr - 8 % Ni - 3 % Mo - Low C)
---------------	---

draad samenstelling									
C	Mn	Si	S	P	Ni	Cr	Mo	V	Cu
0.012	1.5	0.5	0.0007	0.018	8.6	23	3.2	0.05	0.09

draad samenstelling						
N	Nb	Ti	Co	PRE	FN WRC-92	W
0.15	0.01	0.003	0.04	37	55	0.01