

## OK 67.56

Acid rutile coated MMA-electrode for welding lean ferritic-austenitic (duplex) stainless steels. This electrode provides excellent mechanical properties combined with a medium corrosion resistance. It is used for welding the majority of lean duplex types such as S32001 (1.4482), S82011, S32101 (1.4162), S32202 (1.4062), S32304 (1.4362). It can also be used to weld grade S32003 if slightly undermatching corrosion resistance is accepted. It is less suitable for 1.4655 type material where Cu alloying is required. Typical applications are desalination plants, pipes, storage tanks, floodgates, footbridges and containers.

### Specifications

<b>Classifications</b>	EN ISO 3581-A : E Z 23 7 N L R
<b>Approvals</b>	CE : EN 13479

Approvals are based on factory location. Please contact ESAB for more information.

<b>Welding Current</b>	DC+, AC
<b>Ferrite Content</b>	FN 35-65
<b>Alloy Type</b>	Duplex CrNiMoN
<b>Coating Type</b>	Acid Rutile

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
<b>ISO</b>			
As Welded	609 MPa	754 MPa	26 %

### Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
<b>ISO</b>		
As Welded	20 °C	47 J
As Welded	-30 °C	38 J

### Deposition Data

Diameter	Current	Voltage	kg weld metal/kg electrodes	Number of electrodes/kg weld metal	Fusion time per electrode at 90% I max	Deposition Rate
2.5 x 300 mm	50-80 A	25 V	0.61	83	52 sec	0.8 kg/h
3.2 x 350 mm	60-120 A	27 V	0.59	46	58 sec	1.3 kg/h
4.0 x 350 mm	100-170 A	27 V	0.61	29	62 sec	2.0 kg/h