

OK Weartrode 65 T

The electrode deposits a high density of wear resisting carbides in an austenitic matrix capable of resisting extreme conditions of abrasion up to 700 °C. Recovery approximately 220 %. Typical applications include exhaust fans, ash ploughs, conveyor screws and sinter plant components.

Specifications

Classifications	EN 14700 : E Fe16
------------------------	-------------------

Welding Current	DC+
Alloy Type	Austenitic iron
Coating Type	Special

Typical Weld Metal Analysis %

C	Mn	Si	Cr	Mo	V	Nb	W
6.0	0.7	1.9	24.5	6.6	0.8	5.4	1.7

Deposition Data

Diameter	Amps	Volts	Efficiency (Per)	Fusion time per electrode at 90Per I max	Deposition rate at 90Per
3.2 x 350.0 mm	150-170 A	22 V	72 %	132 sec	1.2 kg/h
4.0 x 350.0 mm	220-250 A	23 V	71 %	123 sec	2.0 kg/h