

OK Flux 10.92

OK Flux 10.92 is an agglomerated, Cr-alloying flux which is designed for the butt welding of stainless steels. It can also be used for strip clad-ding with austenitic stainless welding strips. The chromium alloying effect of OK Flux 10.92 compensates for Cr losses in the arc during welding.

Specifications

Classifications	SFA/AWS A5.9 Approvals EN 1207
Approvals	NAKS/HAKC : RD 03-613-03

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	1200 A
Slag Type	Calcium silicate SiO ₂ -MgO-Al ₂ O ₃ -(CaF ₂)
Alloy Transfer	Chromium compensating
Density	nom: 1.0 kg/dm ³
Basicity Index	nom: 1.0

Flux Consumption

Volts	kg Flux / kg Wire DC+
34 V	0.7 kg
30 V	0.55 kg
26 V	0.4 kg
38 V	0.9 kg

Condition : Dimension 4.0 mm , Amps 580 A , Travel speed 33 m/h

Classifications

Wire	AWS/EN	AWS - As Welded
OK Autrod 16.97	14343-A:S 18 8 Mn	-
OK Autrod 308L	A5.9:ER308L/ 14343-A:S 19 9 L	-
OK Autrod 309L	A5.9:ER309L/ 14343-A:S 23 12 L	A5.39: F85A4-ER309L/309L
OK Autrod 316L	A5.9:ER316L/ 14343-A:S 19 12 3 L	A5.39: F80A10-ER316L/316L
OK Autrod 318	A5.9:ER318/ 14343-A:S 19 12 3 Nb	-
OK Autrod 347	A5.9:ER347/ 14343-A:S 19 9 Nb	-

Approvals

Combined with Wire	VdTÜV	BV
OK Autrod 308L	•	-
OK Autrod 316L	•	•
OK Autrod 318	•	-
OK Autrod 347	•	-

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
OK Autrod 16.97									
0.04	5.0	0.95	0.01	0.02	8.5	18.8	0.1	-	-
OK Autrod 308L Current: DC+, 420A, 27V									
0.02	1.0	0.9	-	-	10.0	20.0	-	-	-
OK Autrod 309L									
0.02	1.2	0.7	0.01	0.02	12.9	22.6	0.04	0.01	0.08
OK Autrod 316L									
0.02	1.1	0.7	0.01	0.02	11.6	18.1	2.5	0.15	0.05

OK Flux 10.92

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
OK Autrod 318									
0.035	1.2	0.5	-	-	12.0	18.5	2.6	0.2	-
OK Autrod 347 Current: DC+, 420 A, 27 V									
0.040	0.9	0.75	-	-	9.7	19.8	-	-	-

Typical Weld Metal Analysis %

Nb		FN WRC-92
OK Autrod 309L		
-		7
OK Autrod 316L		
0.01		7
OK Autrod 318		
0.3		-
OK Autrod 347 Current: DC+, 420 A, 27 V		
0.5		9

Typical Wire Composition %

C	Mn	Si	Ni	Cr	Mo	Cu	N	Nb	FN WRC-92
OK Autrod 16.97									
0.07	6.5	0.4	8.2	18.9	-	-	-	-	-
OK Autrod 308L									
0.02	1.9	0.4	9.8	19.8	-	-	0.05	-	-
OK Autrod 309L									
0.02	1.8	0.4	13.4	23.2	0.10	0.1	0.05	-	10
OK Autrod 316L									
0.01	1.7	0.4	12.0	18.2	2.6	-	0.04	-	7
OK Autrod 318									
0.04	1.8	0.4	11.5	18.9	2.6	-	0.04	0.7	11
OK Autrod 347									
0.04	1.4	0.4	9.5	19.2	-	-	0.05	0.6	7

Typical Mechanical Properties

Combined with Wire	Condition	Yield Strength	Tensile Strength	Elongation	Charpy V-Notch
OK Autrod 16.97	As Welded DC+	450 MPa (65 ksi)	630 MPa (91 ksi)	42 %	60 J @ 20 °C (44 ft-lb @ 68 °F) 55 J @ -20 °C (41 ft-lb @ -4 °F) 45 J @ -60 °C (33 ft-lb @ -76 °F)
OK Autrod 308L	As Welded DC+	365 MPa (53 ksi)	580 MPa (84 ksi)	38 %	60 J @ -60 °C (44 ft-lb @ -76 °F) 50 J @ -110 °C (37 ft-lb @ -166 °F)
OK Autrod 309L	As Welded DC+	440 MPa (64 ksi)	600 MPa (87 ksi)	30 %	55 J @ -20 °C (41 ft-lb @ -4 °F) 50 J @ -40 °C (37 ft-lb @ -40 °F)
OK Autrod 316L	As Welded DC+	415 MPa (60 ksi)	570 MPa (83 ksi)	32 %	55 J @ -70 °C (41 ft-lb @ -94 °F)

OK Flux 10.92

Typical Mechanical Properties

Combined with Wire	Condition	Yield Strength	Tensile Strength	Elongation	Charpy V-Notch
OK Autrod 318	As Welded	440 MPa (64 ksi)	600 MPa (87 ksi)	42 %	100 J @ 20 °C (74 ft-lb @ 68 °F) 90 J @ -60 °C (67 ft-lb @ -76 °F) 40 J @ -110 °C (30 ft-lb @ -166 °F)
OK Autrod 347	As Welded DC+	470 MPa (68 ksi)	640 MPa (93 ksi)	35 %	65 J @ 20 °C (48 ft-lb @ 68 °F) 55 J @ -60 °C (41 ft-lb @ -76 °F) 40 J @ -110 °C (30 ft-lb @ -166 °F)