

## Exaton 347

347L is a niobium stabilized chromium-nickel strip electrode used for electro-slag welding (ESW) or submerged arc welding (SAW) to deposit a second layer corrosion resistant alloy of stabilized 19%Cr/9%Ni composition on carbon- and low alloyed steels. The buffer layer is deposited using an over-alloyed consumable, such as 309LNb or 309LNb.

### Specifications

#### Classifications

EN ISO 14343-A : B 19 9 Nb  
SFA/AWS A5.9 : EQ347

### Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.02	1.8	0.4	<=0.02	<=0.02	10.5	20	<=0.3	<=0.3	-

### Typical Wire Composition %

Nb	FN WRC-92
0.5	11