

Exaton AXT (GMAW)

Exaton AXT is a filler metal with increased manganese content, reducing the risk for fissuring / hot cracking that otherwise can be a problem in fully austenitic weld metals. It is suitable for joining work-hardenable steels, armor plates, austenitic stainless manganese steels and stainless or steels with max 18% Cr.

Specifications	ons			
Classifications	EN ISO 14343 : G 18 8 Mn SFA/AWS A5.9 : ER(307) modified			
Approvals	CE : EN 13479 CWB DB : 43.118.10			

Approvals are based on factory location. Please contact ESAB for more information.

Typical Tensile Properties					
Condition	Yield Strength	Tensile Strength	Elongation		
As Welded	460 MPa (67 ksi)	650 MPa (94 ksi)	41 %		

Typical Charpy V-Notch Properties	cal Charpy V-Notch Properties				
Condition	Testing Temperature	Impact Value			
As Welded	20 °C (68 °F)	140 J (104 ft-lb)			
As Welded	-196 °C (-321 °F)	27 J (20 ft-lb)			

Typical Wire	Typical Wire Composition %								
С	Mn	Si	S	Р	Ni	Cr	Мо	Cu	N
0.08	7	0.9	<=0.015	<=0.025	8	18	<=0.3	<=0.1	<=0.06