

SPOOLARC U515

Designed for use on low alloy steels up to 1.25% Cr - 0.5% Mo. Applications include process piping, heat exchangers and pressure vessel fabrication.

Specifications

Classifications	ASME SFA 5.23 : EB2R AWS A5.23 : EB2R
Industry	Process Pressure Vessels

Alloy Type

Low alloy - 1.25% Cr - 0.5% Mo

Typical Wire Composition %

C	Mn	Si	S	P	Cr	Mo
0.10	0.70	0.15	0.01	0.01	1.20	0.47