

ALTIGWELD 5554

Alloy 5554 was developed as a filler Alloy, primarily for Alloy 5454 that is widely used in the Manufacture of chemical storage tanks, and in Particular, those that may be subjected to Temperatures in Excess of 150° F. This combination of Alloys does not become sensitive to stress corrosion cracking (SCC) at elevated temperatures.

Caractéristiques	
Classements	AWS A5.10
Agréments	CWB

Les approbations sont basées sur l'emplacement de l'usine. Veuillez contacter ESAB pour plus d'informations.

Type d'alliage	Aluminum
----------------	----------

composition du fil							
Mn	Si	Cr	Cu	Ti	Zn	Fe	Mg
0.7	0.1	0.1	0.01	0.15	0.01	0.1	2.7