

Coreshield 15

Coreshield 15 is an all-position self-shielded flux cored welding wire for single pass applications. Coreshield 15 produces smooth arc action, full slag coverage, easy slag removal, and low spatter. The use of DCEN (electrode negative) current minimizes the risk of burn-through. Coreshield 15 is excellent for use on lap and fillet welds on thin gauge galvanized and mild steels in all welding positions. The availability of .030" (0.8 mm) diameter makes it possible to use this product on materials as thin as 18 gauge (1.2 mm). The wire is particularly suitable for thin gauge materials 0.030 - 3/16" (0.8-5.0 in.) in galvanized, zinc-aluminum carbon, or aluminised carbon steels. In structural fabrications, the product can be used where no seismic requirements are present.

Caractéristiques	
Classements	SFA/AWS A5.20 : E71T-14/GS JIS Z 3313 : YFW-S50GB KS D 7104 : YFW-S50GB

Courant de soudage	DC-
Type d'alliage	C Mn
Gaz de protection	None

Propriétés de traction typiques	
Condition	Résistance la traction
Brut de soudage	614 MPa

Analyse du métal déposé			
C	Mn	Si	Al
0.23	0.70	0.40	1.98

Caractéristique de dépôt					
Diamètre	Ampères	Volts	Vitesse de dévidage	TTW Dist.	Taux de dépôt
0.8 mm	75-120 A	14-17 V	2.0-10.0 m/min		0.4-1.8 kg/h
0.9 mm	80-120 A	15-17 V	2.06-9.95 m/min	9.5 mm	0.4-2.0 kg/h
1.2 mm	95-150 A	15-18 V	1.37-3.56 m/min	12.5 mm	0.4-1.2 kg/h
1.6 mm	160-275 A	17-19 V	1.42-3.35 m/min	16.0 mm	1.0-2.4 kg/h

Paramètres de soudage	
Diamètre du fil	
0.8 mm	