

OK Tigrod 18.22

Bare welding rods suitable for welding of aluminium alloys with more than 3 % Mg, e.g. AlMg4.5Mn, AlMg5Mn and AlMg5Cr, where high tensile strength is required. Can also be used for materials of type AlMgSiCu and AlSi1MgMn and weldable AlZnMg-alloys, like AlZn4.5Mg1. The welding rods have small additions of Zr which increases the finegrained structure of weld deposit and makes it less sensitive to hot cracking during welding.

Alloy Type	Alloyed aluminium (Al + 6 % Mg + 0.8 % Mn + Ti + Zr)
Shielding Gas	I1, I2, I3 (EN ISO 14175)

Tensile Properties			
Testing Condition	Yield Strength	Tensile Strength	Elongation
As Welded	160 MPa	330 MPa	25 %

Charpy Testing		
Testing Condition	Testing Temp	Impact Value
As Welded	20 °C	26 J

Typical Wire Composition %						
Mn	Si	Al	Cu	Ti	Zr	Mg
0.8	0.06	92.93	0.03	0.03	0.1	5.8