

OK 55.00

OK 55.00 is a reliable, high-quality, LMA electrode, particularly suitable for welding high strength low-alloy steels. The good, low-temperature impact strength of the weld metal should be noted. The weld metal is also very resistant to hot cracking. The electrode is also suitable for welding high strength ships steel, grades A, D and E. Tested according to NACE TM0177 and TM0284. Diffusible Hydrogen tested in various conditions show values below 3 ml/100g.

Especificaciones	
Clasificaciones	SFA/AWS A5.1 : E7018-1H4 R CSA W48 : E4918-1-H4 EN ISO 2560-A : E 46 5 B 32 H5
Aprobaciones	ABS : 4YQ420 H5 BV : 3Y H5 CE : EN 13479 CWB : E4918-1-H4 DB : 10.039.03 DNV-GL : 3Y H5 LR : 3Y H5 UKCA : EN 13479 VdTÜV : 00632

Las aprobaciones se basan en la ubicación de la fábrica. Póngase en contacto con ESAB para obtener más información.

Corriente de soldadura	AC, DC+
Hidrógeno Difusible	< 4.0 ml/100g
tipo de aleación	Carbon Manganese
Tipo de revestimiento	Basic covering

Propiedades típicas de Tensión			
Condición	Límite de flujo	Resistencia a la tracción	Alargamiento
ISO			
Como queda soldado	500 MPa	590 MPa	28 %

Teste Charpy		
Condición	Temperatura de prueba	Valor de impacto
AWS		
Como queda soldado	-45 °C	105 J
ISO		
Como queda soldado	-50 °C	100 J

% típico de análisis de metal de soldadura		
C	Mn	Si
0.06	1.5	0.5

Depósito					
Diámetro	Corriente	Tensión	Eficiencia	Tiempo de fusión por electrodo al 90% I max	Tasa de deposición a 90 % I máx
2.5 x 350.0 mm	80-110 A	23 V	64 %	64 sec	0.9 kg/h
3.2 x 350.0 mm	110-140 A	23 V	62 %	72 sec	1.2 kg/h
3.2 x 450.0 mm	110-140 A	24 V	69 %	88 sec	1.4 kg/h
4.0 x 350.0 mm	140-200 A	23 V	62 %	72 sec	1.77 kg/h
4.0 x 450.0 mm	140-200 A	24 V	70 %	94 sec	2.0 kg/h

OK 55.00

Depósito					
Diámetro	Corriente	Tensión	Eficiencia	Tiempo de fusión por electrodo al 90% I max	Tasa de deposición a 90 % I máx
5.0 x 450.0 mm	200-270 A	24 V	72 %	94 sec	3.0 kg/h
6.0 x 450.0 mm	215-360 A	25 V	72 %	98 sec	4.0 kg/h