

OK Tigrod 2209

Bare corrosion resisting Duplex welding rods for welding of austenitic-ferritic stainless alloys of 22% Cr 5% Ni 3% Mo types. OK Tigrod 2209 has a high general corrosion resistance. In media containing chloride and hydrogen sulphide the alloy has a high resistance to intergranular, pitting and especially to stress corrosion. The alloy is used in a variety of applications across all industrial segments.

Specifikace	
Klasifikace	EN ISO 14343-A : W 22 9 3 N L SFA/AWS A5.9 : ER2209
Schválení	CE : EN 13479 DB : 1.2-3.2mm DNV-GL : 2.0-4.0mm UKCA : EN 13479 VdTÜV : 1.2-3.2mm

Schválení jsou založena na umístění závodu. Pro více informací kontaktujte ESAB.

Typ legování	Austenitic-ferritic (22.5 % Cr - 8 % Ni - 3 % Mo - Low C)
Ochranný plyn	I1, I2, I3, N2 (EN ISO 14175)

Typické vlastnosti v tahu			
Podmínky	Mez skluzu	Mez pevnosti v tahu	Prodloužení
0.5 hour(s) 1050 °C	450 MPa	730 MPa	34 %
Po svaení	600 MPa	765 MPa	28 %

Vrubová houževnatost		
Podmínky	Testovací teplota	Vrubová houževnatost
	20 °C	130 J
	-20 °C	110 J
	-60 °C	90 J
Po svaení	20 °C	100 J
Po svaení	-20 °C	85 J
Po svaení	-60 °C	60 J

Typické složení drátu %								
C	Mn	Si	Ni	Cr	Mo	N	PRE	FN WRC-92
0.01	1.5	0.5	8.5	22.7	3.2	0.17	35	55