

OK Tigrod NiCrMo-13

Bare Ni-Cr-Mo rods for welding of high alloyed Ni-base materials, 9 %Ni steel and super austenic steels of type 20Cr-25Ni with 4-6 % Mo. Can also be used for welding carbon steel to Ni base steel. The weld metal has a very good toughness and is corrosion resistant over a wide range of applications in oxidizing and reducing media.

Specifikace	
Klasifikace	SFA/AWS A5.14 : ERNiCrMo-13 EN ISO 18274 : S Ni 6059 (NiCr23Mo16)
Schválení	VdTÜV : 12663 (MV)

Schválení jsou založena na umístění závodu. Pro více informací kontaktujte ESAB.

Typ legování	Alloyed nickel (Ni + 23 % Cr + 16 % Mo)
--------------	---

Typické vlastnosti v tahu			
Podmínky	Mez skluzu	Mez pevnosti v tahu	Prodloužení
Po svaení	500 MPa	750 MPa	40 %

Vrubová houževnatost		
Podmínky	Testovací teplota	Vrubová houževnatost
Po svaení	-110 °C	120 J

Typického chemického složení svarového kovu v %									
C	Mn	Si	S	P	Cr	Mo	Al	Co	Fe
0.002	0.15	0.03	0.002	0.003	22.7	15.4	0.15	0.02	0.5

Typické složení drátu %							
C	Mn	Si	Ni	Cr	Mo	Al	Fe
0.01	0.2	0.1	Bal	23.0	16.0	0.3	1.0