

Exaton 50SW

Exaton 50SW is a basic agglomerated flux with low silicon pickup. It gives good slag removal, good tie-ins and a finely rippled surface. It is suitable for welding with either wire or strip electrodes of nickel alloy type. It is particularly suitable for surfacing with Exaton Ni72HP strip electrodes (EQNiCr-3 type). Typical applications for flux Exaton 50SW are found in nuclear and chemical equipment fields. It is also suitable for dissimilar material welding of nickel alloy grades to stainless steel grades.

Specifikace

Klasifikace	EN ISO 14174 : S A AF 2
--------------------	-------------------------

Svaovací proud	900 A (Using 60x0.5 mm strip)
Typ strusky	Fluoride basic CaF ₂ -Al ₂ O ₃ -(TiO ₂)-(MnO)
Hustota	nom: 1.2 Kg/l
Index bazicity	nom: 2.4

Klasifikace

Svaovací drát	AWS/EN
Exaton Ni41Cu	A5.14:ERNiFeCr-1/ 18274:S Ni 8065
Exaton Ni72HP	A5.14:ERNiCr-3/ 18274:S Ni 6082 (NiCr20Mn3Nb)

Schválení

Svaovací drát
*Selected production units only. Please contact ESAB for more information. Visit esab.com to download specific flux/wire combination fact sheets for more details.

Typické složení drátu %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton Ni41Cu									
<=0.025	1.0	<=0.3	<=0.010	<=0.025	>=42.0	23.0	3.0	2.3	-
Exaton Ni72HP									
<=0.03	3.0	0.1	<=0.010	<=0.010	72.5	20.0	<=0.2	<=0.05	<=0.05

Typické složení drátu %

Ti	Co	Fe	Nb+Ta
Exaton Ni41Cu			
-	-	>=22.0	-
Exaton Ni72HP			
0.4	<=0.10	<=1.0	2.6

Typického chemického složení svarového kovu v %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton Ni41Cu									
<=0.030	0.8	0.3	<=0.010	<=0.02	40.0	21.5	2.8	2.1	-
Exaton Ni72HP									
0.01	3.0	0.4	0.005	0.009	72.0	19.6	0.1	0.02	-

Typického chemického složení svarového kovu v %

Ti	Co	Fe	Nb+Ta
Exaton Ni41Cu			
-	-	30.0	-
Exaton Ni72HP			
0.15	0.02	1.0	2.2

Exaton 50SW

Typické mechanické vlastnosti

Svaovací drát	Podmínky	Mez skluzu	Mez pevnosti v tahu	Prodloužení	Zkouška rázem
Exaton Ni72HP	Po svaení	320 MPa	600 MPa	40 %	120 J @ 20 °C 110 J @ -196 °C