

Exaton 20.25.5.LCu

Exaton 20.25.5.LCu welding wire is suitable for joining steels of the 20Cr/25Ni/4.5Mo/1.5Cu type - for example Alleima® 2RK65™ used in many areas of the process industry, such as in the production of acetic acid, sulfuric acid, terephthalic or tartaric acid and vinyl chloride. It is also suitable for use in cooling operations involving sea water or heavily polluted river water. It is used for Submerged Arc Welding combined with Exaton Flux 15W.

Spezifikationen	
Klassifikationen	EN ISO 14343-A : S 20 25 5 Cu L SFA/AWS A5.9 : ER385 Werkstoffnummer : ~1.4519
Zulassungen	CE : EN 13479 UKCA : EN 13479

Zulassungen basieren auf dem Werksstandort. Bitte kontaktieren Sie ESAB für weitere Informationen.

Drahtzusammensetzung								
C	Mn	Si	S	P	Ni	Cr	Mo	Cu
<=0.020	1.8	0.4	<=0.015	<=0.015	25	20	4.5	1.5