

OK Autrod 2209

A continuous solid corrosion resisting Duplex wire for welding of austenitic-ferritic stainless alloys of 22% Cr, 5% Ni, 3% Mo types. OK Autrod 2209 has a high general corrosion resistance. In media containing chloride and hydrogen sulphide the alloy has a high resistance to intergranular, pitting and especially to stress corrosion. The alloy is used in a variety of applications across all industrial segments. OK Autrod 2209 can be used in combination with OK Flux 10.93 or OK Flux 10.94.

Especificações	
Classificações	EN ISO 14343-A : S 22 9 3 N L SFA/AWS A5.9 : ER2209
Aprovações	CE : EN 13479 UKCA : EN 13479 VdTÜV : 12101

As aprovações são baseadas na localização da fábrica. Entre em contato com a ESAB para obter mais informações.

Tipo da Liga	Austenitic-ferritic (22.5 % Cr - 8 % Ni - 3 % Mo - Low C)
--------------	---

Composição Química do Consumível (%)								
C	Mn	Si	Ni	Cr	Mo	N	PRE	FN WRC-92
0.01	1.5	0.5	8.5	22.7	3.2	0.17	35	55