

Filarc C23

Rutile iron-powder electrode with 160 % recovery, depositing very smooth standing fillet welds at high deposition rates.

Specifications	
Classifications	SFA/AWS A5.1 : E7024 EN ISO 2560-A : E 42 0 RR 53
Approvals	ABS : 2Y BV : 2Y CE : EN 13479 DNV-GL : 2 Y LR : 2Y RS : 2Y VdTÜV : 00652

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	AC, DC-
Alloy Type	Carbon Manganese
Coating Type	Rutile thick covering

Deposition Data						
Diameter	Amps	Volts	Efficiency (Per)	Number of electrodes/kg weld metal	Fusion time per electrode at 90Per I max	Deposition rate at 90Per
3.2 x 450.0 mm	130-160 A	27 V	60 %	24	78 sec	1.9 kg/h
4.0 x 450.0 mm	170-210 A	32 V	60 %	17	69 sec	3.1 kg/h
5.0 x 450.0 mm	240-340 A	32 V	60 %	10	77 sec	4.2 kg/h