

OK 53.00

OK 53.00 is a basic electrode with especially good mechanical properties and therefore often used when the requirements are extra tough. The electrode is tolerant to wide variations in the analyses of the base metal . Very stable for root runs.

Specifications	
Classifications	SFA/AWS A5.1 : E7016 EN ISO 2560-A : E 42 4 B 12 H10
Approvals	ABS : 3H10, 3Y BV : 3, 3YH10 CE : EN 13479 DB : 10.039.09 DNV : 3 YH15 GL : 3YH10 LR : 3Y H15 VdTÜV : 00630

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	AC, DC+-
Diffusible Hydrogen	<10.0 ml/100g
Alloy Type	Carbon Manganese
Coating Type	Lime Basic

Tensile Properties		
Yield Strength	Tensile Strength	Elongation
AWS		
ISO		

Charpy Testing	
Testing Condition	Testing Temp
AWS	
As Welded	-30 °C
ISO	
As Welded	-40 °C

Deposition Data						
Diameter	Amps	Volts	kg weld metal/kg electrodes	Number of electrodes/kg weld metal	Fusion time per electrode at 90Per I max	Deposition Rate
2.5 x 350 mm	80-110 A	26 V	0.63	83	53 sec	0.82 kg/h
3.2 x 350 mm	80-150 A	26 V	0.68	48	59 sec	1.28 kg/h
3.2 x 450 mm	80-150 A	26 V	0.65	38	67 sec	1.41 kg/h
4.0 x 450 mm	100-220 A	25 V	0.64	25	70 sec	2.05 kg/h
5.0 x 450 mm	180-320 A	30 V	0.67	16	88 sec	2.62 kg/h