

OK Flux 10.92

OK Flux 10.92 is an neutral, agglomerated Cr-compensating flux designed for strip cladding, butt and fillet welding of stainless and corrosion resistant steel types. Good welding characteristics and easy slag removal.

Specifications	
Classifications	EN ISO 14174 : S A CS 2 57 53 DC
Approvals	NAKS/HAKC : RD 03-613-03

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	1200 A
Slag Type	Calcium silicate SiO ₂ -MgO-Al ₂ O ₃ -(CaF ₂)
Alloy Transfer	Chromium compensating
Density	nom: 1.0 kg/dm ³
Basicity Index	nom: 1.0

Flux Consumption	
Volts	kg Flux / kg Wire DC+
34 V	0.7 kg
30 V	0.55 kg
26 V	0.4 kg
38 V	0.9 kg

Condition : Dimension 4.0 mm , Amps 580 A , Travel Speed 33 m/h

Classifications		
Wire	SFA/AWS - EN ISO	AWS - As Welded
OK Autrod 16.97	14343-A:S 18 8 Mn	-
OK Autrod 308L	A5.9:ER308L/ 14343-A:S 19 9 L	-
OK Autrod 309L	A5.9:ER309L/ 14343-A:S 23 12 L	A5.39: F85A4-ER309L/309L
OK Autrod 316L	A5.9:ER316L/ 14343-A:S 19 12 3 L	A5.39: F80A10-ER316L/316L
OK Autrod 318	A5.9:ER318/ 14343-A:S 19 12 3 Nb	-
OK Autrod 347	A5.9:ER347/ 14343-A:S 19 9 Nb	-

Approvals		
Wire	VdTÜV	BV
OK Autrod 308L	•	-
OK Autrod 316L	•	•
OK Autrod 318	•	-
OK Autrod 347	•	-

Typical Weld Metal Analysis %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
OK Autrod 16.97									
0.04	5.0	0.95	0.01	0.02	8.5	18.8	0.1	-	-
OK Autrod 308L Current: DC+, 420A, 27V									
0.02	1.0	0.9	-	-	10.0	20.0	-	-	-
OK Autrod 309L									
0.02	1.2	0.7	0.01	0.02	12.9	22.6	0.04	0.01	0.08
OK Autrod 316L									
0.02	1.1	0.7	0.01	0.02	11.6	18.1	2.5	0.15	0.05
OK Autrod 318									

OK Flux 10.92

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
0.035	1.2	0.5	-	-	12.0	18.5	2.6	0.2	-
OK Autrod 347 Current: DC+, 420 A, 27 V									
0.040	0.9	0.75	-	-	9.7	19.8	-	-	-

Typical Weld Metal Analysis %

Nb	FN WRC-92
OK Autrod 309L	
-	7
OK Autrod 316L	
0.01	7
OK Autrod 318	
0.3	-
OK Autrod 347 Current: DC+, 420 A, 27 V	
0.5	9

Typical Wire Composition %

C	Mn	Si	Ni	Cr	Mo	Cu	N	Nb	FN WRC-92
OK Autrod 16.97									
0.07	6.5	0.4	8.2	18.9	-	-	-	-	-
OK Autrod 308L									
0.02	1.9	0.4	9.8	19.8	-	-	0.05	-	-
OK Autrod 309L									
0.02	1.8	0.4	13.4	23.2	0.10	0.1	0.05	-	10
OK Autrod 316L									
0.01	1.7	0.4	12.0	18.2	2.6	-	0.04	-	7
OK Autrod 318									
0.04	1.8	0.4	11.5	18.9	2.6	-	0.04	0.7	11
OK Autrod 347									
0.04	1.4	0.4	9.5	19.2	-	-	0.05	0.6	7

Typical Mechanical Properties

Wire	Condition	Yield Strength	Tensile Strength	Elongation	Charpy V-Notch
OK Autrod 16.97	As Welded DC+	450 MPa	630 MPa	42 %	60 J @ 20 °C 55 J @ -20 °C 45 J @ -60 °C
OK Autrod 308L	As Welded DC+	365 MPa	580 MPa	38 %	60 J @ -60 °C 50 J @ -110 °C
OK Autrod 309L	As Welded DC+	440 MPa	600 MPa	30 %	55 J @ -20 °C 50 J @ -40 °C
OK Autrod 316L	As Welded DC+	415 MPa	570 MPa	32 %	55 J @ -70 °C
OK Autrod 318	As Welded	440 MPa	600 MPa	42 %	100 J @ 20 °C 90 J @ -60 °C 40 J @ -110 °C
OK Autrod 347	As Welded DC+	470 MPa	640 MPa	35 %	65 J @ 20 °C 55 J @ -60 °C 40 J @ -110 °C