

OK Flux 10.82

Agglomerated, aluminate-rutile, low basicity flux for Submerged Arc Welding. High welding speeds. For automotive (wheels), general construction, etc. Suitable for single and multi wire procedures, for DC and AC. Due to high Si-alloying intended for a limited number of passes and plate thickness up to about 25 mm.