

## OK Autrodur 38 G M

A copper coated, low-alloyed solid GMAW wire used for hard facing and building up, giving a wear resistant weld metal with a hardness between 35-40 HRC. Used for repair and maintenance of e.g. tracks, rails, wheels, rolls, railcrossings, shafts, shovel teeth and other parts on digging machines, tools like dies etc.

### Specifications

<b>Classifications</b>	EN 14700 : Fe2
<b>Approvals</b>	NAKS/HAKC : 1.2mm

Approvals are based on factory location. Please contact ESAB for more information.

<b>Alloy Type</b>	Low alloyed (0.7 C, 2 % Mn, 1 % Cr, 0.2 % Ti)
<b>Shielding Gas</b>	M12, M21, C1 (EN ISO 14175)

### Typical Wire Composition %

### Typical Weld Metal Analysis %

### Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.0 mm	80-280 A	18-28 V	2.7-14.7 m/min	1.0-5.4 kg/h
1.2 mm	120-350 A	20-33 V	2.7-12.4 m/min	1.5-6.6 kg/h