

FILARC PZ6163

A metal cored wire alloyed with 17%Cr and 1% Mo used with M21 shielding gas.

Specifications

Classifications	EN 14700 : T Fe7
	DIN 8555 : MF5-400GC

Welding Current	DC+
-----------------	-----

Typical Weld Metal Analysis %

C	Mn	Si	Cr	Mo
0.17	0.53	0.83	16.6	1.08

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.6 mm	150-450 A	21-40 V	2.4-11.9 m/min	1.8-9.0 kg/h