

OK Autrod NiCrMo-13

A continuous solid Ni-Cr-Mo electrode for welding of high alloyed Ni-base materials, 9 %Ni steel and super austenitic steels of type 20Cr-25Ni with 4-6 % Mo. Can also be used for welding carbon steel to Ni base steel. The weld metal has a very good toughness and is corrosion resistant over a wide range of applications in oxidizing and reducing media.

Specifications

Classifications	SFA/AWS A5.14 : ERNiCrMo-13 EN ISO 18274 : S Ni 6059 (NiCr23Mo16)
Approvals	VdTÜV : 12662 (MV)

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Alloyed nickel (Ni + 23 % Cr + 16 % Mo)
-------------------	---

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
As Welded	500 MPa	750 MPa	40 %
As Welded	500 MPa	700 MPa	42 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
As Welded	-110 °C	120 J

Typical Wire Composition %

Typical Weld Metal Analysis %

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.0 mm	100-200 A	21-27 V	6.0-13.0 m/min	2.5-5.5 kg/h
1.2 mm	160-280 A	24-30 V	6.0-10.0 m/min	3.6-6.0 kg/h
1.6 mm	200-350 A	25-32 V	4.0-8.0 m/min	4.3-8.6 kg/h