

OK Autrod Ni-1

A continuous solid nickel based electrode alloyed with about 3 % Ti for welding of high purity nickel (min 99.6 %Ni), ordinary wrought nickel and nickel with reduced C content. The weld metal can be used in a wide range of applications where the construction is working with corrosive media.

Specifications

Classifications	SFA/AWS A5.14 : ERNi-1 EN ISO 18274 : S Ni 2061 (NiTi3)
Approvals	VdTÜV : 12658 (MV) VdTÜV : 12664 (FP)

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Nickel (Ni + 2.5 % Ti)
Shielding Gas	I1, I2, I3 (EN 439)

Typical Wire Composition %

Typical Weld Metal Analysis %

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
0.8 mm	70-190 A	20-27 V	5.0-18.0 m/min	1.3-4.8 kg/h
1.0 mm	100-200 A	21-27 V	6.0-13.0 m/min	2.5-5.5 kg/h