RECARGUE DURO
ARCO SUMERGIDO (SAW)



OK Flux 07.29

OK Flux 07.29 is a agglomerated nickel alloying flux desigend for strip cladding with a 17Cr strip. The combination deposits a weld metal with 15Cr4Ni and 350-400 HB. Can also be used for cladding with a 17Cr wire, which deposits the same type of weld metal.