

OK Flux 10.07

Neutral, agglomerated, nickel- and molybdenum alloying flux, specially designed for strip cladding with a 17Cr-strip, producing a weld metal with 14Cr-4Ni-1Mo and a hardness of 370-420 HB. Can also be used for cladding with a 17Cr-wire producing the same weld metal.

Especificaciones

Clasificaciones	EN ISO 14174 : S A GS 3 Ni4 Mo1 DC
Corriente de soldadura	1000 A
Tipo de escoria	Calcium silicate SiO ₂ -MgO-Al ₂ O ₃ -(CaF ₂)
Transferencia de aleación	Nickel and molybdenum alloying
Densidad	nom: 1.0 kg/dm ³
Índice de basicidad	nom: 1.0

El Consumo de Flujo

Voltios
28 V
26 V

Condición : kg Flux / kg Hilo polaridad DC+ 0.65 kg , Dimension 60 x 0.5 mm , Amperios 750 A , Velocidad de desplazamiento 7 m/h

Clasificaciones

Hilo	AWS según EN (Euro Norma)
OK Band 430	14343-A:B 17

Aprobaciones

Hilo
*Selected production units only. Please contact ESAB for more information. Visit esab.com to download specific flux/wire combination fact sheets for more details.

% Análisis metal depositado (valores típicos)

C	Mn	Si	S	P	Ni	Cr	Mo
OK Band 430							
-	-	-	0.01	0.02	-	-	-
OK Band 430 Current: DC+, 770A, 25V, 22 cm/min							
0.05	0.15	0.6	-	-	4.0	13.0	1.0

% Composición hilo (valores típicos)

C	Mn	Si	Cr
OK Band 430			
0.04	0.66	0.4	17.0