

FILARC 88S

A basic coated low hydrogen electrode alloyed with max 1% Ni for the positional welding of higher tensile steels, BS4360-55F steel and similar grades. Good CVN toughness down to -60°C ; CTOD tested in the AW and SR conditions. Many approved welding procedures are available. Use short arc. Weave slowly when permitted. Use DC- for root passes.

Especificaciones	
Clasificaciones	SFA/AWS A5.5 : E8016-G EN ISO 2560-A : E 50 6 Mn1Ni B 12 H5
Aprobaciones	ABS : E8016-G CE : EN 13479 DB : 10.105.16 DNV-GL : 5Y46 H5 LR : 5Y46 H5 RS : 5Y46 H5 VdTÜV : 06107

Las aprobaciones se basan en la ubicación de la fábrica. Póngase en contacto con ESAB para obtener más información.

Corriente de soldadura	AC, DC+(-)
Hidrógeno difusible	< 5.0 ml/100g
Tipo de aleación	Low alloyed (0.9 % Ni)
Tipo de recubrimiento	Basic covering

Propiedades tensoras típicas			
Condición	Límite de elasticidad	Resistencia a la tracción	Alargamiento
ISO			
Como soldado	560 MPa	640 MPa	27 %

Propiedades de Ensayo de impacto Charpy		
Condición	Temperatura de ensayo	Valor de impacto
ISO		
Como soldado	-40 °C	115 J
Como soldado	-60 °C	100 J

% Análisis metal depositado (valores típicos)					
C	Mn	Si	Ni	Cr	Mo
0.06	1.77	0.27	0.9	0.03	0.01

Datos aportación					
Diámetro	Amperios	Voltios	Rendimiento (%)	Tiempo de fusión por electrodo al 90 % I máx.	Tasa de deposición al 90 % I máx.
2.5 x 350.0 mm	55-85 A	25.7 V	61.11 %	51.47 sec	0.96 kg/h
3.2 x 350.0 mm	80-140 A	21.4 V	59 %	69 sec	0.96 kg/h
4.0 x 450.0 mm	110-170 A	21.5 V	62 %	106 sec	1.27 kg/h
5.0 x 450.0 mm	180-230 A	22.6 V	63 %	109 sec	1.95 kg/h