

OK Autrod 308H

A continuous solid corrosion resisting chromium-nickel wire for the welding of austenitic chromium nickel alloys of the 18% Cr - 8% Ni-type. OK Autrod 308H has a good general corrosion resistance. The alloy has a high carbon content which makes this alloy suitable for applications used at higher temperatures. The alloy is used in chemical and food processing industries as well as for pipes, tubes and boilers. OK Autrod 308H can be used in combination with OK Flux 10.93.

Especificaciones

Clasificaciones	EN ISO 14343-A : S 19 9 H SFA/AWS A5.9 : ER308H
Aprobaciones	VdTÜV : 12101

Las aprobaciones se basan en la ubicación de la fábrica. Póngase en contacto con ESAB para obtener más información.

Tipo de aleación	Austenitic 19% Cr - 9% Ni - High C
-------------------------	------------------------------------

% Composición hilo (valores típicos)

C	Mn	Si	Ni	Cr	N	Nb	FN WRC-92
0.05	1.9	0.5	9.2	19.8	0.06	0.01	9