

Exaton 22.8.3.L

Exaton 22.8.3.L is a duplex stainless filler metal for welding duplex stainless steels. Weldability as well as properties of the all-weld metal is excellent. Corrosion resistance is equal to 904L in most applications. Exaton 22.8.3.L is used for welding of duplex stainless steels such as Alleima SAF 2205 and SAF 2304. It can also be used for welding of duplex stainless steels to carbon steel and for cladding. It is used for Submerged Arc Welding and the recommended flux is Exaton 15W.

Especificaciones	
Clasificaciones	EN ISO 14343-A : S 22 9 3 N L SFA/AWS A5.9 : ER2209
Aprobaciones	CE : EN 13479 UKCA : EN 13479

Las aprobaciones se basan en la ubicación de la fábrica. Póngase en contacto con ESAB para obtener más información.

Tipo de aleación	Austenitic-ferritic (22.5 % Cr - 8 % Ni - 3 % Mo - Low C)
------------------	---

% Composición hilo (valores típicos)									
C	Mn	Si	S	P	Ni	Cr	Mo	V	Cu
0.012	1.5	0.5	0.0007	0.018	8.6	23	3.2	0.05	0.09

% Composición hilo (valores típicos)						
N	Nb	Ti	Co	PRE	FN WRC-92	W
0.15	0.01	0.003	0.04	37	55	0.01