

OK Flux 10.72

Agglomerated aluminate-basic flux for Submerged Arc Welding especially for applications with toughness requirements at low temperature. Excellent slag removal also in narrow V-joints. For wind tower productions, pressure vessels, general constructions etc. Extremely high current carrying capacity. For single or multi wire procedures. Suitable for DC and AC welding. Single layer and multi layer welding of unlimited plate thickness.

Tekniset tiedot	
Luokitukset	EN ISO 14174 : S A AB 1 57 AC H5
Hyväksynnät	CE : EN 13479 DB : 51.039.12 UKCA : EN 13479

Hyväksynnät perustuvat tehtaan sijaintiin. Ota yhteyttä ESAB:iin saadaksesi lisätietoja.

Vetypitoisuus	max 5 ml/100g weld metal (Redried flux)
Kuonatyyppe	Aluminate-basic
Seostavuus	No Silicon and moderately Manganese alloying
Tiheys	nom: 1.2 kg/dm ³
Emäksisyys	nom: 1.9

Jauheenkulutus		
Jännite	Jauheen kulutus lankakiloa kohti DC+	Jauheen kulutus lankakiloa kohti AC
34 V	1.3 kg	1.2 kg
30 V	1.0 kg	0.9 kg
26 V	0.7 kg	0.6 kg
38 V	1.6 kg	1.4 kg

Tila : Ulottuvuus Ø 4.0 mm , A 580 A , Siirtonopeus 55 cm/min

Luokittelut				
Lanka	AWS / EN	EN - Hitsatussa tilassa	AWS - hitsatussa tilassa	AWS - lämpökäsiteltynä
Spoolarc 29S	A5.17:EM13K	-	-	-
OK Autrod 12.20	A5.17:EM12/ 14171-A:S2	14171-A: S 38 5 AB S2	A5.17: F7A8-EM12	A5.17: F6P8-EM12
OK Autrod 12.22	A5.17:EM12K/ 14171-A:S2Si	14171-A: S 42 5 AB S2Si	A5.17: F7A8-EM12K	A5.17: F6P8-EM12K
OK Autrod 12.24	A5.23:EA2/ 14171-A:S2Mo; 24598-A:S S Mo	14171-A: S 46 3 AB S2Mo	A5.23: F8A5-EA2-A3	A5.23: F8P5-EA2-A3
OK Autrod 13.24	A5.23:ENi6/ 14171-A:S3Ni1Mo0,2	-	-	-
OK Autrod 13.27	A5.23:ENi2/ 14171-A:S2Ni2	14171-A: S 46 6 AB S2Ni2	A5.23: F8A8-ENi2-Ni2	A5.23: F7P8-ENi2-Ni2
OK Autrod 13.62	A5.23:EG/ 14171-A:SZ3TiB	-	-	-
OK Autrod 13.64	A5.23:EA2TiB/ 14171-A:S2MoTiB	-	A5.23: F8TA8-EA2TiB	-

Hyväksynnät						
Lanka	CWB	CE	DB	VdTÜV	ABS	DNV
Spoolarc 81	•	-	-	-	-	-
OK Autrod 12.20	-	•	•	•	-	-
OK Autrod 12.22	-	•	•	•	•	•
OK Autrod 12.24	-	•	•	•	-	-
OK Autrod 13.27	-	•	-	-	-	-

OK Flux 10.72

Hitsiaineen Koostumus									
C	Mn	Si	S	P	Ni	Cr	Mo	V	Al
Spoolarc 29S Stress Relieved 1 hr. @ 1150°F									
0.06	1.96	0.56	0.012	0.017	0.05	0.08	0.03	0.005	0.016
Spoolarc 29S As Welded									
0.06	1.96	0.56	0.012	0.017	0.05	0.08	0.03	0.005	0.016
Spoolarc 75 As Welded									
0.07	1.84	0.55	0.005	0.016	0.84	0.04	0.01	0.008	-
Spoolarc ENi4 As Welded									
0.08	1.47	0.34	0.006	0.013	1.62	0.05	0.15	-	-
OK Autrod 12.20 AC, 580A, 29V									
0.06	1.4	0.2	-	-	-	-	-	-	-
OK Autrod 12.20 DC+, 580A, 29V									
0.05	1.5	0.2	-	-	-	-	-	-	-
OK Autrod 12.22 AC, 580A, 29V									
0.08	1.4	0.3	-	-	-	-	-	-	-
OK Autrod 12.22 DC+, 580A, 29V									
0.05	1.5	0.3	-	-	-	-	-	-	-
OK Autrod 12.24 AC, 580A, 29V									
0.06	1.5	0.2	-	-	-	-	0.5	-	-
OK Autrod 12.24 DC+, 580A, 29V									
0.05	1.6	0.2	-	-	-	-	0.5	-	-
OK Autrod 13.27 AC, 580A, 29V									
0.07	1.4	0.30	-	-	2.2	-	-	-	-
OK Autrod 13.27 DC+, 520A, 29V									
0.05	1.4	0.30	-	-	2.2	-	-	-	-

Hitsiaineen Koostumus			
Cu	Nb	Ti	Co
Spoolarc 29S Stress Relieved 1 hr. @ 1150°F			
0.122	0.002	0.004	0.009
Spoolarc 29S As Welded			
0.122	0.002	0.004	0.009
Spoolarc 75 As Welded			
0.080	-	0.002	-
Spoolarc ENi4 As Welded			
0.060	-	-	-

Langan Koostumus									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	Ti
Spoolarc 29S									
0.08	1.15	0.5	0.006	0.013	-	-	-	0.06	-
Spoolarc 71									
0.10	1.22	0.55	0.01	0.01	-	-	-	-	0.07
Spoolarc 75									
0.08	0.89	0.46	0.01	0.00	0.98	0.04	0.01	0.07	-
Spoolarc 81									
0.09	0.95	0.26	0.01	0.01	-	-	-	-	-

OK Flux 10.72

Langan Koostumus

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	Ti
Spoolarc ENi4									
0.17	0.73	0.19	0.00	0.00	1.74	-	0.17	0.06	-
OK Autrod 12.20									
0.10	1.06	0.07	-	-	-	-	-	-	-
OK Autrod 12.22									
0.09	1.01	0.19	-	-	-	-	-	-	-
OK Autrod 12.24									
0.09	1.08	0.14	-	-	-	-	0.48	-	-
OK Autrod 13.24									
0.12	1.52	0.23	-	-	0.88	-	0.19	-	-
OK Autrod 13.27									
0.10	1.02	0.14	-	-	2.19	-	-	-	-
OK Autrod 13.62									
0.07	1.55	0.28	-	-	-	-	0.01	-	0.14
OK Autrod 13.64									
0.07	1.22	0.28	-	-	-	-	0.49	-	0.14

Langan Koostumus

B									
OK Autrod 13.62									
0.013									
OK Autrod 13.64									
0.013									

Tyypilliset mekaaniset ominaisuudet

Lanka	Tila	Myötöraja	Murtolujuus	Venymä	Charpy V -iskutkeys
Spoolarc 29S	Hitsatussa tilassa	532 MPa	622 MPa	25 %	57 J @ -40 °C 43 J @ -46 °C 41 J @ -51 °C
Spoolarc 75	Hitsatussa tilassa	556 MPa	646 MPa	28 %	91 J @ -40 °C 83 J @ -51 °C
Spoolarc 81	Hitsatussa tilassa	415 MPa	500 MPa	30 %	119 J @ -29 °C 100 J @ -40 °C 71 J @ -51 °C 50 J @ -62 °C
Spoolarc ENi4	Hitsatussa tilassa	607 MPa	677 MPa	27 %	141 J @ -40 °C 107 J @ -51 °C 88 J @ -62 °C
OK Autrod 12.20	Hitsatussa tilassa AWS DC+	415 MPa	500 MPa	30 %	125 J @ -30 °C 100 J @ -40 °C 70 J @ -50 °C 50 J @ -62 °C
OK Autrod 12.20	Hitsatussa tilassa EN AC	420 MPa	500 MPa	33 %	140 J @ -30 °C 130 J @ -40 °C 80 J @ -50 °C
OK Autrod 12.22	Hitsatussa tilassa AWS DC+	440 MPa	530 MPa	31 %	120 J @ -30 °C 100 J @ -40 °C 70 J @ -50 °C 50 J @ -62 °C
OK Autrod 12.22	Hitsatussa tilassa EN	425 MPa	560 MPa	27 %	140 J @ -30 °C

OK Flux 10.72

Tyypilliset mekaaniset ominaisuudet					
Lanka	Tila	Myötöraja	Murtolujuus	Venymä	Charpy V -iskutkeys
	AC				130 J @ -40 °C 80 J @ -50 °C
OK Autrod 12.24	Hitsatussa tilassa AWS DC+	500 MPa	590 MPa	25 %	60 J @ -30 °C 40 J @ -40 °C 35 J @ -46 °C
OK Autrod 12.24	Hitsatussa tilassa EN AC	535 MPa	600 MPa	24 %	70 J @ -30 °C 50 J @ -40 °C 40 J @ -50 °C
OK Autrod 13.24	Hitsatussa tilassa AWS DC+	530 MPa	660 MPa	28 %	90 J @ 0 °C 35 J @ -40 °C
OK Autrod 13.27	Hitsatussa tilassa EN AC	520 MPa	610 MPa	27 %	120 J @ -30 °C 100 J @ -40 °C 80 J @ -50 °C 60 J @ -60 °C
OK Autrod 13.27	Hitsatussa tilassa AWS DC+	490 MPa	610 MPa	30 %	100 J @ -40 °C 80 J @ -51 °C 50 J @ -62 °C
OK Autrod 13.62	Hitsatussa tilassa (acc. AWS) Plate thickness: 12mm; Heat Input: 2.2kJ/mm; Side 1: 600A, 32V, 53cm /min; Side 2: 700A, 32V, 60cm/min; DC+	500 MPa	610 MPa	27 %	50 J @ -62 °C
OK Autrod 13.64	Hitsatussa tilassa (acc. to AWS) Plate thickness 12mm Heat input 2.2kJ/mm 700A, 32V, 60cm/min DC+	560 MPa	660 MPa	27 %	50 J @ -62 °C