

Exaton 49S

Exaton 49S is a basic, agglomerated flux for electrosag strip surfacing. This flux is particularly intended for high-speed welding. In spite of high welding speed, flux Exaton 49S gives excellent slag removal and bead appearance, also for niobium-alloyed strip electrodes. It is used together with strip electrodes of the chromium, chromium-nickel and chromium-nickel-molybdenum steel types with or without niobium. Exaton 49S gives the following typical chemical properties of all-weld metal for the strip electrode below. Exaton 24.13.LNb is used for corrosion resistant weld surfacing of components in the chemical, petrochemical, nuclear industry. Typical components are pressure vessels, heat exchangers, shafts, industrial piping etc.

Tekniset tiedot	
Luokitukset	EN ISO 14174 : ES A FB 2B
Hitsausvirta	2200 A (Using 60x0.5 mm strip)
Kuonatyyppe	Fluoride basic CaF ₂ -Al ₂ O ₃
Tiheys	nom: 1.0 Kg/l
Emäksisyys	nom: 4.4

Luokittelut	
Lanka	AWS / EN
Exaton 19.12.3.L	A5.9:EQ316L/ 14343-A:B 19 12 3 L
Exaton 19.13.4.L	A5.9:EQ317L/ 14343-A:B 19 13 4 L
Exaton 19.9.L	A5.9:EQ308L/ 14343-A:B 19 9 L
Exaton 19.9.LNb	A5.9:EQ347/ 14343-A:B 19 9 Nb
Exaton 21.11.LNb	A5.9:EQ?309LNb?/ 14343-A:B 22 11 L Nb
Exaton 22.11.L	A5.9:EQ(309L)/ 14343-A:B 22 11 L
Exaton 24.13.L	A5.9:EQ309L/ 14343-A:B 23 12 L
Exaton 24.13.LNb	A5.9:EQ?309LNb?/ 14343-A:B 23 12 Nb

Hyväksynät	
Lanka	
*Selected production units only. Please contact ESAB for more information. Visit esab.com to download specific flux/wire combination fact sheets for more details.	

Langan Koostumus									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L									
<=0.020	1.8	0.4	<=0.020	<=0.020	13	18.5	2.9	<=0.3	-
Exaton 19.13.4.L									
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	-
Exaton 19.9.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	10	20	<=0.3	<=0.1	-
Exaton 19.9.LNb									
<=0.02	1.8	0.4	<=0.02	<=0.02	10.5	20	<=0.3	<=0.3	-
Exaton 21.11.LNb									
<=0.015	1.8	0.2	<=0.020	<=0.020	11	21	<=0.3	<=0.3	-
Exaton 22.11.L									
<=0.015	1.8	0.2	<=0.020	<=0.020	11.5	21	<=0.3	<=0.1	-
Exaton 24.13.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	13	23.5	<=0.3	<=0.1	-
Exaton 24.13.LNb									
<=0.02	2	0.3	<=0.020	<=0.020	12.5	24	<=0.3	<=0.3	-

Exaton 49S

Langan Koostumus		
Nb	Ferrite FN	FN WRC-92
Exaton 19.12.3.L		
-	-	8
Exaton 19.13.4.L		
-	-	7
Exaton 19.9.L		
-	-	12
Exaton 19.9.LNb		
0.5	-	11
Exaton 21.11.LNb		
0.55	-	14
Exaton 22.11.L		
-	13	-
Exaton 24.13.L		
-	-	15
Exaton 24.13.LNb		
0.75	-	22

Hitsiaineen Koostumus									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L Layer 1 with "24.13.L"									
<=0.03	-	-	-	-	12.0	17.7	2.2	-	-
Exaton 19.13.4.L Layer 1 with "24.13.L"									
<=0.03	-	-	-	-	13.0	18.5	2.7	-	-
Exaton 19.9.L Layer 1 with "24.13.L"									
<=0.03	-	-	-	-	10	19.2	-	-	-
Exaton 19.9.LNb (Layer 1 with "24.13.L" & Layer 2 with "19.9.LNb")									
0.02	1.3	0.3	-	-	10.6	19.5	0.1	-	0.03
Exaton 19.9.LNb (Layer 1 with "24.13.LNb" & Layer 2 with "19.9.LNb")									
0.02	1.4	0.3	-	-	10.5	19.6	0.1	-	0.03
Exaton 19.9.LNb									
-	-	-	-	-	-	-	-	-	-
Exaton 21.11.LNb (1 layer)									
0.02	1.4	0.4	-	-	9.7	18.9	0.1	-	0.05
Exaton 21.11.LNb									
-	-	-	-	-	-	-	-	-	-
Exaton 24.13.L									
<=0.07	-	-	-	-	10.2	19	-	-	-
Exaton 24.13.LNb									
<=0.06	-	-	-	-	9.7	18.5	-	-	-

Hitsiaineen Koostumus	
Nb	FN WRC-92
Exaton 19.12.3.L Layer 1 with "24.13.L"	
-	6
Exaton 19.13.4.L Layer 1 with "24.13.L"	
-	6

Exaton 49S

Hitsiaineen Koostumus	
Nb	FN WRC-92
Exaton 19.9.L Layer 1 with "24.13.L"	
-	8
Exaton 19.9.LNb (Layer 1 with "24.13.L" & Layer 2 with "19.9.LNb")	
0.3	-
Exaton 19.9.LNb (Layer 1 with "24.13.LNb" & Layer 2 with "19.9.LNb")	
0.4	-
Exaton 21.11.LNb (1 layer)	
0.5	-
Exaton 24.13.L	
-	6
Exaton 24.13.LNb	
-	5