

Exaton 25.22.2.LMnB

Exaton 25.22.2.LMnB is a chromium-nickel-molybdenum covered electrode with basic coating for welding of austenitic stainless steels for example, Sandvik 2RE69 and Sandvik 3R60 U.G used in the production of ammonium carbamate, nitric acid and inorganic acids. It is also used for surfacing on low alloyed steels. The electrode combines good welding properties such as arc stability, low spatter and self peeling slag with very low impurity levels. The fully austenitic weld metal (maximum 0.6% ferrite) is very resistant to hot cracking. Exaton 25.22.2.LMn is used for welding of Sandvik 2RE69 and Sandvik 3R60 U.G. urea grade materials. But it can also be used for the following types: ISO 1.4466, 1.4335, 1.4435, 1.4436, 1.4477, 1.4578 and 1.4585; UNS S31050, S31002, S31603 and S31600.

Tekniset tiedot

Luokitukset	EN ISO 3581-A : E 25 22 2 N L B 12 SFA/AWS A5.4 : (E310Mo-15)
--------------------	--

Hitsausvirta	DC+
Ferriittipitoisuus	FN 0
Seostyyppi	25Cr 22Ni 2Mo N
Päällystetyyppi	Basic

Tyypilliset lujuusarvot

Tila	Myötöraja	Murtolujuus	Venymä
ISO			
Hitsatussa tilassa	420 MPa	600 MPa	30 %

Charpy V -iskusitkeys

Tila	Testauslämpötila	Iskusitkeys
ISO		
Hitsatussa tilassa	20 °C	70 J

Hitsiaineen Koostumus

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.04	4.5	0.4	<=0.020	<=0.020	22	25	2.1	0.05	0.14

Hitsiaineen Koostumus

FN WRC-92
0

Hitsausarvot

Halkaisija	A	Hyötyluku (%)	Puikon palo aika 90% maksivirralla	Sulatusnopeus 90 % I max
2.5 x 300.0 mm	60-80 A			0.0 kg/h
3.2 x 350.0 mm	80-110 A	64 %	55 sec	1.7 kg/h
4.0 x 350.0 mm	110-140 A	53 %	75 sec	2.3 kg/h