

## OK Tigrod 12.62

A tripple desoxidized copper coated rod designed for GTAW of mild and fine grained structural- and pressure vessel steels as well as ship building steels. The rod is capable of producing high quality welds in semi-killed and rimmed steel as well as steel of various carbon levels. Because of added desoxidants, Al-Ti-Zr, the rod can also be used for welding steels with a rusty or dirty surface, without any sacrifice of weld quality.

Specifications	
Classifications	EN ISO 636-A : W 46 4 2Ti EN ISO 636-A : W2Ti SFA/AWS A5.18 : ER70S-2
Approvals	CE : EN 13479 UKCA : EN 13479

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Carbon-manganese steel
Shielding Gas	I1 (EN ISO 14175)

Typical Tensile Properties				
Condition	Yield Strength	Tensile Strength	Elongation	
Ar (I1) EN				
As Welded	570 MPa	625 MPa	26 %	

Typical Charpy V-Notch Properties			
Condition	Testing Temperature	Impact Value	
Ar (I1) EN			
As Welded	-40 °C	180 J	

Typical Wire Composition %			
С	Mn	Si	
0.06	1.1	0.6	

Typical Weld Metal Analysis %				
С	Mn	Si	s	P
0.05	1.11	0.72	0.012	0.013