

Exaton 10SW

Exaton 10SW is a chromium-compensating agglomerated flux giving good slag removal and a fine bead appearance. It is suitable for welding with wire and strip electrodes of the chromium & chromium-nickel and chromium-nickel-molybdenum steel types either with or without niobium. Exaton 10SW is an all round flux which can be used for many applications varying from surfacing continuous caster rolls to large components in chemical plants.

Specifications	
Classifications	EN ISO 14174 : S A CS 2 Cr
Welding Current	1200 A (Using 60x0.5 mm strip)
Slag Type	Calcium silicate SiO ₂ -MgO-Al ₂ O ₃ -(CaF ₂)
Density	nom: 1.0 kg/l
Basicity Index	nom: 1.0

Flux_Consumption_SAW	
Volts	DC+ Weight
34 V	0.7 kg
30 V	0.55 kg
26 V	0.4 kg
38 V	0.9 kg

Condition : Dimension 4.0 mm , Amps 580 A , Travel Speed 33 m/h

Classifications_SAW		
Wire	AWS/EN	AWS - As Welded
Exaton 19.12.3.L	A5.9:ER316L/ 14343-A:S 19 12 3 L	A5.39: F80A10-ER316L/316L
Exaton 19.12.3.L	A5.9:EQ316L/ 14343-A:B 19 12 3 L	-
Exaton 19.13.4.L	A5.9:EQ317L/ 14343-A:B 19 13 4 L	-
Exaton 19.9.L	A5.9:ER308L/ 14343-A:S 19 9 L	-
Exaton 19.9.L	A5.9:EQ308L/ 14343-A:B 19 9 L	-
Exaton 19.9.LNb	A5.9:EQ347/ 14343-A:B 19 9 Nb	-
Exaton 19.9.Nb	A5.9:ER347/ 14343-A:S 19 9 Nb	-
Exaton 21.13.3.L	A5.9:EQ(309LMo)/ 14343-A:B 21 13 3 L	-
Exaton 22.8.3.L	A5.9:EQ2209/ 14343-A:B 22 9 3 N L	-
Exaton 24.13.L	A5.9:EQ309L/ 14343-A:B 23 12 L	-
Exaton 24.13.LNb	A5.9:EQ?309LNb?/ 14343-A:B 23 12 Nb	-

Approvals_SAW	
Wire	VdTÜV
Exaton 19.9.L	•
Exaton 19.9.LNb	•
Exaton 19.9.Nb	•
Exaton 22.8.3.L	•

Typical Weld Metal Analysis %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L (Layer 1 with "24.13.L" & Layer 2 with "19.12.3.L")									
0.02	0.8	0.7	-	-	11.5	19.0	2.2	-	0.06
Exaton 19.13.4.L Layer 1 with "21.13.3.L"									
<=0.04	-	-	-	-	13	18.5	3.3	-	-
Exaton 19.9.L 1st layer with "24.13.L"									
<=0.03	-	-	-	-	10.0	19.7	-	-	-

Exaton 10SW

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.9.LNb (Layer 1 with "24.13.LNb")									
0.02	0.8	0.6	-	-	10.4	21.0	0.0	-	0.05
Exaton 19.9.Nb Layer 1 with "24.13.LHF" & 2 layers with "19.9.Nb"									
0.04	0.6	1.0	0.01	0.01	9.2	19.0	0.01	0.1	0.06
Exaton 22.8.3.L Layer 1 with "24.13.L" & 2 layers with "22.8.3.L"									
<=0.03	-	-	-	-	8.5	22.7	2.9	-	0.16
Exaton 24.13.L Layer 1 with "24.13.L"									
<=0.07	-	-	-	-	10.5	19.2	-	-	-
Exaton 24.13.LNb									
<=0.06	-	-	-	-	9.7	19.2	-	-	-

Typical Weld Metal Analysis %

Nb	FN WRC-92	Nb+Ta
Exaton 19.12.3.L (Layer 1 with "24.13.L" & Layer 2 with "19.12.3.L")		
0	-	-
Exaton 19.13.4.L Layer 1 with "21.13.3.L"		
-	5	-
Exaton 19.9.L 1st layer with "24.13.L"		
-	8	-
Exaton 19.9.LNb (Layer 1 with "24.13.LNb")		
0.3	-	-
Exaton 19.9.Nb Layer 1 with "24.13.LHF" & 2 layers with "19.9.Nb"		
0.3	-	0.3
Exaton 22.8.3.L Layer 1 with "24.13.L" & 2 layers with "22.8.3.L"		
-	40	-
Exaton 24.13.L Layer 1 with "24.13.L"		
-	6	-
Exaton 24.13.LNb		
-	6	-

Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L									
<=0.020	1.8	0.4	<=0.020	<=0.020	13	18.5	2.9	<=0.3	-
Exaton 19.13.4.L									
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	-
Exaton 19.9.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	10	20	<=0.3	<=0.1	-
Exaton 19.9.LNb									
<=0.02	1.8	0.4	<=0.02	<=0.02	10.5	20	<=0.3	<=0.3	-
Exaton 19.9.Nb									
0.04	1.3	0.35	0.012	0.015	9.5	19.5	0.03	0.11	0.06
Exaton 21.13.3.L									
<=0.015	1.8	0.2	<=0.015	<=0.020	13.5	20.5	2.9	<=0.3	-
Exaton 22.8.3.L									
<=0.020	1.6	0.5	<=0.015	<=0.020	9	23	3.1	-	0.15
Exaton 24.13.L									

Exaton 10SW

Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.015	1.8	0.35	<=0.015	<=0.015	13	23.5	<=0.3	<=0.1	-
Exaton 24.13.LNb									
<=0.02	2	0.3	<=0.020	<=0.020	12.5	24	<=0.3	<=0.3	-

Typical Wire Composition %

Nb	Co	FN deLong	FN WRC	FN WRC-92	Nb+Ta
Exaton 19.12.3.L					
-	-	-	-	8	-
Exaton 19.13.4.L					
-	-	-	-	7	-
Exaton 19.9.L					
-	-	-	-	12	-
Exaton 19.9.LNb					
0.5	-	-	-	11	-
Exaton 19.9.Nb					
0.6	0.1	5	5	-	0.6
Exaton 21.13.3.L					
-	-	-	-	13	-
Exaton 22.8.3.L					
-	-	-	-	50	-
Exaton 24.13.L					
-	-	-	-	15	-
Exaton 24.13.LNb					
0.75	-	-	-	22	-

SAW_Typical_Mech_Properties

Wire	Testing Condition	Yield Strength	Tensile Strength	Elongation	Charpy V-Notch Result
Exaton 19.12.3.L	As Welded	420 MPa	580 MPa	32 %	69 J @ 20 °C 60 J @ -40 °C 55 J @ -70 °C 50 J @ -196 °C
Exaton 19.9.L	As Welded	400 MPa	580 MPa	38 %	69 J @ 20 °C 59 J @ -40 °C 40 J @ -196 °C
Exaton 19.9.Nb	As Welded Joining	440 MPa	625 MPa	38 %	72 J @ 20 °C 61 J @ -40 °C 34 J @ -196 °C