

## Dual Shield II 712X

Dual Shield II 712X is an all-position flux cored wire intended for applications requiring outstanding weld metal toughness. This X Series wire, in combination with 75% Argon/25% CO2 shielding gas, can produce Charpy V-Notch impact results of more than 40 ft-lb (68 J) at -60°F (-51°C) and Crack Tip Opening Displacement (CTOD) results of more than 20 mils (0.5 mm) at -40°F (-40°C). Dual Shield II 712X also provides the smooth arc and low spatter levels characteristic of Dual Shield flux cored wires. Applications include off-shore oil components, shipbuilding and heavy equipment where exceptional Charpy impact/low temperature toughness is required.

| Specifications  |   |
|-----------------|---|
| Classifications | ASME SFA 5.36<br>ASME SFA 5.20<br>AWS A5.36 : E71T1-M21A6-CS2-H8<br>AWS A5.20 : E71T-1MJH8/T-9MJH8/T-12MJH8 |
| Approvals       | ABS<br>CWB : W48 E491T-12MJ-H8<br>DNV-GL<br>LR  |
| Industry        | Heavy Equipment<br>Ship/Barge Building<br>Offshore Oil  |

Approvals are based on factory location. Please contact ESAB for more information.

| Tensile_Properties |                |                  |            |  |  |  |
|--------------------|----------------|------------------|------------|--|--|--|
| Testing Condition  | Yield Strength | Tensile Strength | Elongation |  |  |  |
| 75% Ar - 25% CO2   |                |                  |            |  |  |  |
| As Welded          | 540 MPa        | 570 MPa          | 28 %       |  |  |  |

| Charpy Testing    |                           |       |  |  |  |
|-------------------|---------------------------|-------|--|--|--|
| Testing Condition | ng Condition Testing Temp |       |  |  |  |
| 75% Ar - 25% CO2  |                           |       |  |  |  |
| As Welded         | -40 °C                    | 125 J |  |  |  |
| As Welded         | -51 °C                    | 62 J  |  |  |  |
| As Welded         | -18 °C                    | 175 J |  |  |  |

| Typical Weld Metal Analysis % |     |     |       |       |  |  |  |
|-------------------------------|-----|-----|-------|-------|--|--|--|
| C                             | Mn  | Si  | S     | Ρ     |  |  |  |
| 75% Ar - 25% CO2              |     |     |       |       |  |  |  |
| 0.05                          | 1.1 | 0.3 | 0.010 | 0.009 |  |  |  |