

## Dual Shield Prime 81Ni1 H4

A seamless, copper free, cored wire designed to weld thick steel components. The diffusible hydrogen level is consistently below 4ml/100g of deposited weld metal and with the seam of the wire being laser welded this ensures no moisture pick up. The wire is not copper coated which means there is no chance of copper flakes contaminating feed liners, torches and contact tips. Dual Shield Prime 81Ni1 H4 is designed to weld high strength steels (>500 MPa, >72 ksi yield strength) and provides excellent impact toughness down to -60 degrees C. Dual Shield Prime 81Ni1 H4 is designed to be used with CO<sub>2</sub> (C1) shielding gas mixture.

### Specifications

<b>Classifications</b>	EN ISO 17632-B : T556T1-1CA-N2-U-H5 SFA/AWS A5.29 : E81T1-Ni1C H4 EN ISO 17632-A : T 50 6 1Ni P C1 1 H5
<b>Approvals</b>	ABS : 5YQ460SA H5 BV : SA5Y46 H5 CE : EN 13479 DNV-GL : V Y46MS(H5) LR : 5Y46S H5 RS : 5Y46S H5 UKCA : EN 13479

Approvals are based on factory location. Please contact ESAB for more information.

<b>Welding Current</b>	DC+
<b>Diffusible Hydrogen</b>	< 4 ml/100g
<b>Alloy Type</b>	C Mn Ni
<b>Shielding Gas</b>	C1 (EN ISO 14175)

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
<b>C1 Shielding gas</b>			
As Welded	525 MPa	605 MPa	27 %

### Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
<b>C1 Shielding gas</b>		
As Welded	-60 °C	65 J
As Welded	-40 °C	120 J

### Typical Weld Metal Analysis %

C	Mn	Si	Ni
<b>C1 Shielding gas</b>			
0.04	1.30	0.25	0.92

### Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.2 mm	170-310 A	23-35 V	6.0-16.5 m/min	2.5-6.2 kg/h
1.4 mm	180-400 A	23-38 V	4.0-13.5 m/min	2.6-7.1 kg/h
1.6 mm	180-420 A	24-38 V	3.0-13.0 m/min	1.8-7.5 kg/h