

Exaton 20.25.5.LCu

Exaton 20.25.5.LCu welding wire is suitable for joining steels of the 20Cr/25Ni/4.5Mo/1.5Cu type - for example Alleima® 2RK65™ used in many areas of the process industry, such as in the production of acetic acid, sulfuric acid, terephthalic or tartaric acid and vinyl chloride. It is also suitable for use in cooling operations involving sea water or heavily polluted river water. It is used for Submerged Arc Welding combined with Exaton Flux 15W.

Mszaki leírás	
Osztályozások	EN ISO 14343-A : S 20 25 5 Cu L SFA/AWS A5.9 : ER385 Werkstoffnummer : ~1.4519
Jóváhagyások	CE : EN 13479 UKCA : EN 13479

A jóváhagyások a gyár helyén alapulnak. További információért forduljon az ESAB-hoz.

Huzal összetétel								
C	Mn	Si	S	P	Ni	Cr	Mo	Cu
<=0.020	1.8	0.4	<=0.015	<=0.015	25	20	4.5	1.5