

Exaton 10SW

Exaton 10SW is a chromium-compensating agglomerated flux giving good slag removal and a fine bead appearance. It is suitable for welding with wire and strip electrodes of the chromium & chromium-nickel and chromium-nickel-molybdenum steel types either with or without niobium. Exaton 10SW is an all round flux which can be used for many applications varying from surfacing continuous caster rolls to large components in chemical plants.

Mszaki leírás	
Osztályozások	EN ISO 14174 : S A CS 2 Cr

Hegesztési áramerősség	1200 A (Using 60x0.5 mm strip)
Salaktípus	Calcium silicate SiO ₂ -MgO-Al ₂ O ₃ -(CaF ₂)
Srség	nom: 1.0 kg/l
Bázikussági index	nom: 1.0

Fedpor-felhasználás	
Feszültség	kg Flux / kg Huzal DC+
34 V	0.7 kg
30 V	0.55 kg
26 V	0.4 kg
38 V	0.9 kg

?llapot : Méret 4.0 mm , Amper 580 A , Haladási sebesség 33 m/h

Besorolások		
Huzal	AWS/EN	AWS - heg. ?llapot
Exaton 19.12.3.L	A5.9:ER316L/ 14343-A:S 19 12 3 L	A5.39: F80A10-ER316L/316L
Exaton 19.12.3.L	A5.9:EQ316L/ 14343-A:B 19 12 3 L	-
Exaton 19.13.4.L	A5.9:EQ317L/ 14343-A:B 19 13 4 L	-
Exaton 19.9.L	A5.9:ER308L/ 14343-A:S 19 9 L	-
Exaton 19.9.L	A5.9:EQ308L/ 14343-A:B 19 9 L	-
Exaton 19.9.LNb	A5.9:EQ347/ 14343-A:B 19 9 Nb	-
Exaton 19.9.Nb	A5.9:ER347/ 14343-A:S 19 9 Nb	-
Exaton 21.13.3.L	A5.9:EQ(309LMo)/ 14343-A:B 21 13 3 L	-
Exaton 22.8.3.L	A5.9:EQ2209/ 14343-A:B 22 9 3 N L	-
Exaton 24.13.L	A5.9:EQ309L/ 14343-A:B 23 12 L	-
Exaton 24.13.LNb	A5.9:EQ?309LNb?/ 14343-A:B 23 12 Nb	-

Jóváhagyások	
Huzal	VdTÜV
Exaton 19.9.L	•
Exaton 19.9.LNb	•
Exaton 19.9.Nb	•
Exaton 22.8.3.L	•

Huzal összetétel									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L									
<=0.020	1.8	0.4	<=0.020	<=0.020	13	18.5	2.9	<=0.3	-
Exaton 19.13.4.L									
<=0.02	1.5	0.4	<=0.020	<=0.020	14	19	3.6	<=0.3	-
Exaton 19.9.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	10	20	<=0.3	<=0.1	-

Exaton 10SW

Huzal összetétel									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.9.LNb									
<=0.02	1.8	0.4	<=0.02	<=0.02	10.5	20	<=0.3	<=0.3	-
Exaton 19.9.Nb									
0.04	1.3	0.35	0.012	0.015	9.5	19.5	0.03	0.11	0.06
Exaton 21.13.3.L									
<=0.015	1.8	0.2	<=0.015	<=0.020	13.5	20.5	2.9	<=0.3	-
Exaton 22.8.3.L									
<=0.020	1.6	0.5	<=0.015	<=0.020	9	23	3.1	-	0.15
Exaton 24.13.L									
<=0.015	1.8	0.35	<=0.015	<=0.015	13	23.5	<=0.3	<=0.1	-
Exaton 24.13.LNb									
<=0.02	2	0.3	<=0.020	<=0.020	12.5	24	<=0.3	<=0.3	-

Huzal összetétel					
Nb	Co	FN deLong	FN WRC	FN WRC-92	Nb+Ta
Exaton 19.12.3.L					
-	-	-	-	8	-
Exaton 19.13.4.L					
-	-	-	-	7	-
Exaton 19.9.L					
-	-	-	-	12	-
Exaton 19.9.LNb					
0.5	-	-	-	11	-
Exaton 19.9.Nb					
0.6	0.1	5	5	-	0.6
Exaton 21.13.3.L					
-	-	-	-	13	-
Exaton 22.8.3.L					
-	-	-	-	50	-
Exaton 24.13.L					
-	-	-	-	15	-
Exaton 24.13.LNb					
0.75	-	-	-	22	-

Varratfém analízis									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
Exaton 19.12.3.L (Layer 1 with "24.13.L" & Layer 2 with "19.12.3.L")									
0.02	0.8	0.7	-	-	11.5	19.0	2.2	-	0.06
Exaton 19.13.4.L Layer 1 with "21.13.3.L"									
<=0.04	-	-	-	-	13	18.5	3.3	-	-
Exaton 19.9.L 1st layer with "24.13.L"									
<=0.03	-	-	-	-	10.0	19.7	-	-	-
Exaton 19.9.LNb (Layer 1 with "24.13.LNb")									
0.02	0.8	0.6	-	-	10.4	21.0	0.0	-	0.05
Exaton 19.9.Nb Layer 1 with "24.13.LHF" & 2 layers with "19.9.Nb"									
0.04	0.6	1.0	0.01	0.01	9.2	19.0	0.01	0.1	0.06
Exaton 22.8.3.L Layer 1 with "24.13.L" & 2 layers with "22.8.3.L"									

Exaton 10SW

Varratfém analízis

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.03	-	-	-	-	8.5	22.7	2.9	-	0.16
Exaton 24.13.L Layer 1 with "24.13.L"									
<=0.07	-	-	-	-	10.5	19.2	-	-	-
Exaton 24.13.LNb									
<=0.06	-	-	-	-	9.7	19.2	-	-	-

Varratfém analízis

Nb	FN WRC-92	Nb+Ta
Exaton 19.12.3.L (Layer 1 with "24.13.L" & Layer 2 with "19.12.3.L")		
0	-	-
Exaton 19.13.4.L Layer 1 with "21.13.3.L"		
-	5	-
Exaton 19.9.L 1st layer with "24.13.L"		
-	8	-
Exaton 19.9.LNb (Layer 1 with "24.13.LNb")		
0.3	-	-
Exaton 19.9.Nb Layer 1 with "24.13.LHF" & 2 layers with "19.9.Nb"		
0.3	-	0.3
Exaton 22.8.3.L Layer 1 with "24.13.L" & 2 layers with "22.8.3.L"		
-	40	-
Exaton 24.13.L Layer 1 with "24.13.L"		
-	6	-
Exaton 24.13.LNb		
-	6	-

Jellegzetes mechanikai tulajdonságok

Huzal	?llapot	Folyáshatár	Szakítószilárdság	Szakadási nyúlás	Charpy-féle V vizsgálat
Exaton 19.12.3.L	Hegesztett állapot	420 MPa	580 MPa	32 %	69 J @ 20 °C 60 J @ -40 °C 55 J @ -70 °C 50 J @ -196 °C
Exaton 19.9.L	Hegesztett állapot	400 MPa	580 MPa	38 %	69 J @ 20 °C 59 J @ -40 °C 40 J @ -196 °C
Exaton 19.9.Nb	Hegesztett állapot Joining	440 MPa	625 MPa	38 %	72 J @ 20 °C 61 J @ -40 °C 34 J @ -196 °C