

OK Flux 10.87

Agglomerated, aluminate-rutile, low basicity flux for Submerged Arc Welding. Perfect wetting in butt-, overlap- and fillet welds. High welding speeds. For air compressor tanks, LPG bottles, general construction, automotive, etc. Suitable for single and multi wire procedures, for DC and AC. Intended for a limited number of passes and plate thicknesses up to about 25 mm.

Specifiche	
Classificazioni	EN ISO 14174 : S A AR 1 95 AC
Tipo di scoria	Aluminate-rutile
Trasferimento lega	Very high Silicon alloying, neutral on Manganese
Densit	nom: 1.2 kg/dm ³
Indice di basicit	nom: 0.4
Dimensioni grano	0.2-1.6 mm (10x65 mesh)

Consumo di Flusso		
Volt	kg flusso/ kg filo DC+	kg flusso/ kg filo AC
34 V	1.2 kg	1.0 kg
30 V	0.9 kg	0.7 kg
26 V	0.6 kg	0.5 kg
38 V	1.5 kg	1.3 kg

Stato : Dimension Ø 4.0 mm , Amp 580 A , Velocit di avanzamento 55 cm/min

Classificazioni				
filo	SFA/AWS - EN ISO	EN-come saldato	AWS-come saldato	AWS-Trattamento termico post saldatura
OK Autrod 12.10	A5.17:EL12/ 14171-A:S1	14171-A: S 35 A AR S1	A5.17: F6AZ-EL12	A5.17: F6PZ-EL12
OK Autrod 12.20	A5.17:EM12/ 14171-A:S2	14171-A: S 42 A AR S2	A5.17: F7AZ-EM12	A5.17: F6PZ-EM12
OK Autrod 12.22	A5.17:EM12K/ 14171-A:S2Si	14171-A: S 42 A AR S2Si	A5.17: F7AZ-EM12K	A5.17: F6PZ-EM12K

Approvazioni	
filo	
*Selected production units only. Please contact ESAB for more information. Visit esab.com to download specific flux/wire combination fact sheets for more details.	

analisi tipica del deposito		
C	Mn	Si
OK Autrod 12.10 DC+, 580A, 29V		
0.05	0.6	0.8
OK Autrod 12.10 AC, 580A, 29V		
0.06	0.5	0.7
OK Autrod 12.20 AC, 580A, 29V		
0.06	0.9	0.7
OK Autrod 12.20 DC+, 580A, 29V		
0.05	1.0	0.8
OK Autrod 12.22 AC, 580A, 29V		
0.06	0.9	0.8
OK Autrod 12.22 DC+, 580A, 29V		
0.05	1.0	0.9

OK Flux 10.87

Proprietà meccaniche tipiche					
filo	Stato	Resistenza allo snervamento	Resistenza alla trazione	Allungamento	Intaglio a V Charpy
OK Autrod 12.10	Come saldato AWS DC+	370 MPa	470 MPa	25 %	50 J @ 20 °C 25 J @ 0 °C
OK Autrod 12.10	Come saldato EN AC	390 MPa	460 MPa	25 %	70 J @ 20 °C 45 J @ 0 °C
OK Autrod 12.20	Come saldato EN AC	450 MPa	520 MPa	25 %	80 J @ 20 °C 45 J @ 0 °C
OK Autrod 12.20	Come saldato AWS DC+	410 MPa	500 MPa	25 %	50 J @ 20 °C 25 J @ 0 °C
OK Autrod 12.22	Come saldato EN AC	450 MPa	520 MPa	25 %	90 J @ 20 °C 50 J @ 0 °C 90 J @ 20 °C 50 J @ 0 °C
OK Autrod 12.22	Come saldato AWS DC+	420 MPa	510 MPa	25 %	50 J @ 20 °C 25 J @ 0 °C